

STUDIO MARM  
SEDIMENT STONE

STONESOURCE

# STUDIO MARMI **SEDIMENT STONE**



The grainy linear effect draws inspiration from sandy soils and it's enhanced with shiny mineral speckles, totally brought out in the lappato finish. The softness of details and natural colors of the matter are the pure expression of a timeless elegance.

Studio Marmi Sediment Stone stands out because of its high performances in terms of strength and durability, without losing its' sophisticated beauty.



**WHITE**



**SAND**



**TAUPE**



**LIGHT GREY**




**OLIVE GREY**



**BLACK**

MADE IN  
**USA**





**FLOOR**  
OLIVE GREY Lappato 18"x36" Rectified + WHITE 12"x24" Rectified



**FLOOR**  
OLIVE GREY Lappato 18"x36" Rectified + WHITE 12"x24" Rectified



**WALL**

BLACK Lappato 12"x24" Rectified + BLACK Mosaic Honed 12"x12" (2"x2" Pcs)

**FLOOR**

LIGHT GREY Lappato 18"x36" Rectified



**FLOOR**  
LIGHT GREY Lappato 18"x36" Rectified



WALL  
BLACK Lappato 12"x24" Rectified + BLACK Mosaic Honed 12"x12" (2"x2" Pcs)



**FLOOR**  
BLACK Honed 18"x36" Rectified

**WALL**  
BLACK Honed 12"x24" Rectified + BLACK Mosaic Honed 12"x12" (1"x2" Pcs)



**FLOOR**  
BLACK Honed 18"x36" Rectified



**WALL**

BLACK Honed 12"x24" Rectified + BLACK Mosaic Honed 12"x12" (1"x2" Pcs)



**FLOOR**  
TAUPE + SAND + WHITE Honed 12"x24" Rectified



**FLOOR**  
TAUPE + SAND + WHITE Honed 12"x24" Rectified



**FLOOR**  
SAND 12"x24" Rectified



FLOOR  
SAND 12"x24" Rectified



**FLOOR**  
WHITE Honed 18"x36" Rectified

**WALL**  
OLIVE GREY Honed 12"x24" Rectified + OLIVE GREY Mosaic Honed 12"x12" (2"x2" Pcs)



**FLOOR**  
WHITE Honed 18"x36" Rectified



WALL  
OLIVE GREY Honed 12"x24" Rectified + OLIVE GREY Mosaic Honed 12"x12" (2"x2" Pcs)

# STUDIO MARMI **SEDIMENT STONE**

## COLOR AVAILABILITY

**WHITE**



**SAND**



**TAUPE**




**LIGHT GREY**




**OLIVE GREY**



**BLACK**



## SIZE AVAILABILITY



**18"x36" Rectified**

*Thickness: 8mm - Finish: Honed/Lappato  
Available in all colors*




**12"x24" Rectified**

*Thickness: 8mm - Finish: Honed  
Available in all colors*

# STUDIO MARMI SEDIMENT STONE


## DECORS

**Mosaic 12"x12" (2"x2" Pcs)**  
*Thickness: 8mm - Finish: Honed*



*Available in all colors*

**Mosaic 12"x12" (1"x2" Pcs)**  
*Thickness: 8mm - Finish: Honed*




*Available in all colors*

## SPECIAL PIECES



**Bullnose 4"x24" Rectified**  
*Thickness: 8mm - Finish: Honed*  
*Available in all colors*



**Cove Base 6"x12" Rectified**  
*Thickness: 7.5mm - Finish: Honed*  
*Available in all colors*

## PACKAGING


ITEM	PCS/BOX	SF/BOX	BOX/PAL	SF/PAL	WEIGHT LB/SF
18"x36"	5	22.189	18	339.402	3.63
12"x24"	8	15.751	32	504.032	3.55
					<b>lb per pieces</b>
Mosaic 12"x12" (2"x2" Pcs)	5	4.896	-	-	3.55
Mosaic 12"x12" (1"x2" Pcs)	5	4.896	-	-	3.55
Bullnose 4"x24"	16	10.388	-	-	2.00
Cove Base 6"x12"	8	3.876	-	-	1.70

# STUDIO MARMI SEDIMENT STONE

## TECHNICAL CHARACTERISTICS

Glazed Porcelain Stoneware	Classiification in accordance with	ANSI A137.1-2012	P1 Impervious Porcelain Tiles
PHYSICAL-CHEMICAL PROPERTIES	STANDARD OF TEST	REQUIRED VALUE	AVERAGE VALUE
Sizes - Rectified	ASTM C499	Range of Thickness: $\pm 0.040$ Inc. Max.	$\leq \pm 0.04$ Inc.
	ASTM C499	Average Facial Dimension: $\pm 0.25\%$	$\leq \pm 0.25\%$
	ASTM C485	Warpage Average Edge: $\pm 0.40\%$	$\leq \pm 0.40\%$
	ASTM C485	Warpage Average Diagonal: $\pm 0.40\%$	$\leq \pm 0.40\%$
	ASTM C502	Wedging: $\pm 0.25\%$	$\leq \pm 0.25\%$
Water Absorption	ASTM C373	$E \leq 0.5\%$	$\leq 0.1\%$
Bond Strength	ASTM C482	50 psi or greater	$\geq 200$ psi
Visible Abrasion Resistance	ASTM C1027	According to manufacturer's data	Class 4
Hardness (MOHS)	Scratch Test (No regulated)	Range 0-10	$\geq 7$
Resistance to Thermal Shock	-	Test method available	Guaranteed
Frost Resistance	ASTM C1026	No sample must show alterations to surface	No evidence of damage
Chemical Resistance	ASTM C650	No requirements / Range E-A	Class A
Stain Resistance	ASTM C1378	No requirements / Range E-A	Class A
Breaking Strength	ASTM C648	250 ibf or greater	$\geq 400$ ibf
Aesthetic Classification	Visual Evaluation Shade & Texture	No requirements / Range V0-V4	V2
D.C.O.F.	ANSI A 137.1-2012 (BOT 3000)	$\geq 0.42$ Wet	Honed: $\geq 0.42$ Wet

MADE IN  
USA



STUDIO MARMİ SEDIMENT STONE

11.2021.v2

