Milliken.

OBEX™ TILE: CUT

Entrance Flooring

Construction

Tufted, Cut Pile

Tile Size

50 cm x 50 cm (19.7" x 19.7")
Designs: Contour / Fiber / Fizz /
Footpath / Stipple / Thread

25 cm x 1 m (9.84" x 39.37")

Design: Grain

Yarn Type

Milliken-Certified WearOn® Nylon and Monofilament

Dye Method

PrintWorks[™] Precision Dye

Tufted Face Weight

 $28 \text{ oz/yd}^2 (949 \text{ g/m}^2)$

Gauge

5/32

Stitches Per Inch

5.6

Tufts

35.8/in² (554/100 cm²)

Finished Pile Height

0.182" (4.62 mm)

Average Density (Finished)

5,281

Standard Backing

PVC-Free WellBAC® Comfort Plus Cushion

Recycled Content by Total Weight

36.2% Pre-Consumer, 0.0% Post-Consumer

Embodied Carbon

21.15 (kg CO₂e)/m²

Nominal Total Thickness

0.50" (12.7 mm)

Nominal Total Weight

 $130.0 \text{ oz/yd}^2 (4,407 \text{ g/m}^2)$

Flammability (Radiant Panel

ASTM-E-648)

≥ 0.45 (Class I)

Smoke Density (NFPA-258-T or

ASTM-E-662)

≤ 450

Methenamine Pill Test (CPSC FF-1-70

or **ASTM D** 2859

Self-Extinguishing

Lightfastness (AATCC 16E)

 ≥ 4.0 at 80 Hours

Crocking (AATCC 165)

≥ 4.0 Wet or Dry

Static Electricity (AATCC-134) 20%

R.H.,70° F.

≤ 3.5 KV, Permanent Conductive Fiber

Recommended Maintenance

Daily Vacuum, Deep Clean via Hot

Water Extraction

Indoor Air Quality—CRI Green Label

Plus™

GLP0793, Carpet Category 5Y

Recommended Installation Method(s)

Monolithic, Quarter-Turn, Ashlar

Pieces Per Box

12 Tiles, 32.29 ft² (3.0 m²) Designs: Contour / Fiber / Fizz /

Footpath / Stipple / Thread

8 Tiles, 21.53 ft2 (2.0 m2

Design: Grain

Installation Zone Application

Zone 2 or Zone 3

ADA / BS8300 / ISO 21542 Compliant

WARRANTIES

Lifetime Face Fiber Wear Lifetime Antistatic Lifetime Floor Compatibility Lifetime Color Pattern Permanency Lifetime Floor Release Lifetime Cushion Resiliency

Lifetime Moisture Resistance
Lifetime Delamination of Backing
Lifetime Staining/Soiling (StainSmart®)
Lifetime Dimensional Stability
Lifetime Tuft Bind
Lifetime Edge Ravel

This cushion-back carpet tile product is covered by one or more patents, published applications and/or patents pending. Specifications are subject to normal manufacturing tolerances and may be changed without prior notice. Copies of actual test results are available upon request.









