## Milliken

## OBEX<sup>TM</sup> TILE: LOOP

Entrance Flooring

Construction

Tufted, Multi-Level Loop

Tile Size

50 cm x 50 cm (19.7" x 19.7")

**Yarn Type** 

ECONYL® Solution-Dyed Nylon and Solution-Dyed Nylon Monofilament

**Dye Method** 

Solution Dyed

**Tufted Face Weight** 

 $27.9 \text{ oz/yd}^2 (946 \text{ g/m}^2)$ 

Gauge

1/12

**Stitches Per Inch** 

11.3

**Tufts** 

135.6/in<sup>2</sup> (2,100/100 cm<sup>2</sup>)

**Finished Pile Height** 

0.255" (6.48 mm)

**Average Density (Finished)** 

5,740

**Standard Backing** 

PVC-Free WellBAC® Comfort Cushion

Available with TractionBack®

**Recycled Content by Total Weight** 

33.3% Pre-Consumer, 6.6% Post-Consumer

**Embodied Carbon** 

 $8.89 (kg CO_2e)/m^2$ 

**Nominal Total Thickness** 

0.391" (9.9 mm)

**Nominal Total Weight** 

 $104.2 \text{ oz/yd}^2 (3,533 \text{ g/m}^2)$ 

Flammability (Radiant Panel ASTM-E-648)

≥ 0.45 (Class I)

Smoke Density (NFPA-258-T or

**ASTM-E-662)** 

≤ 450

Methenamine Pill Test (CPSC FF-1-70 or ASTM D 2859

Self-Extinguishing

**Lightfastness (AATCC 16E)** 

≥ 4.0 at 80 Hours

**Crocking (AATCC 165)** 

 $\geq$  4.0 Wet or Dry

Static Electricity (AATCC-134) 20% R.H.,70° F.

≤ 3.5 KV, Permanent Conductive Fiber

**Recommended Maintenance** 

Daily Vacuum, Deep Clean via Hot

Water Extraction

Indoor Air Quality—CRI Green Label

Plus'"

GLP7205, Carpet Category 13X

**Recommended Installation Method(s)** 

Monolithic, Quarter-Turn, Ashlar

**Pieces Per Box** 

12 Tiles, 32.29 ft<sup>2</sup> (3.0 m<sup>2</sup>)

**Installation Zone Application** 

Zone 2 or Zone 3

ADA / BS8300 / ISO 21542 Compliant

## **WARRANTIES**

Lifetime Face Fiber Wear Lifetime Antistatic Lifetime Floor Compatibility Lifetime Color Pattern Permanency Lifetime Floor Release Lifetime Cushion Resiliency

Lifetime Moisture Resistance
Lifetime Delamination of Backing
Lifetime Staining/Soiling (StainSmart®)
Lifetime Dimensional Stability
Lifetime Tuft Bind
Lifetime Edge Ravel

This cushion-back carpet tile product is covered by one or more patents, published applications and/or patents pending. Specifications are subject to normal manufacturing tolerances and may be changed without prior notice. Copies of actual test results are available upon request.









