## L'ANTIC COLONIAL

Model: AC4 NATURAL 1L OAT

Codes: 100245531 Group: G-207

Format: 7 153/256"X50 121/256"X81/256" approx.



| COMPOSITION |         |      |                  |  |  |  |
|-------------|---------|------|------------------|--|--|--|
|             |         | Size | Material         | Type of material                                       |  |  |
|             | Layer 1 | 0.2  | Melamine         | Aminoplastic thermosetting resins                      |  |  |
|             | Layer 2 | 0.2  | Decorative paper |  |  |  |
|             | Layer 3 | 7.5  | HDF              | High-density Fiber Board and water-repellent glues     |  |  |
|             | Layer 4 | 0.1  | Backside         | Sheets of kraft paper impregnated with phenolic resins |  |  |

## **CERTIFICATIONS**

CARB: Phase II compliant Carb certification

## **FEATURES**



Imitates the surface of wood



Gloss-free



20 year warranty for domestic use valid for laminate floors that have been installed in rooms where they are exposed to normal wear and tear for their recommended End Use Category in accordance with EN 13329.



Format where only one board has been used to finish the entire base surface



Floor capable of dissipating excess electrical charges and distribute them over its





It is one of the easiest to install and safest systems in the market. We just need to adjust the board to be installed longitudinally to the one already placed, by applying a soft pressure without the need for any type of tool. Both pieces will fit and will be secured thanks to the safety tab. It is just as simple to take apart, which market for a wild filescent blue. which makes for a quick disassembly



32. General commercial



Beveled cut on all 4 edges of the board for emphasizing size



Installation system where gluing the boards to the floor is not necessary. They are placed on a foam, joined together, as long as the product does not already have a foil on the back of the piece.



5 year warranty for commercial use valid for laminate floors that have been installed in rooms where they are exposed to normal wear and tear for their recommended End Use Category in accordance with EN 13329.



Is suitable for installing on water radiant heating



PanEuropean Forest Certification that guarantees to consumers the origin of the products from sustainably managed forests



23. Intensive residential



Abrasion-resistance level as per Standard UNE-EN 13329





It is advisable to follow the installation and maintenance instructions published by L'ANTIC COLONIAL, S.A.U., observing in any case the legal or regulatory requirements that may exist for each area of use. Do not use aggressive cleaning agents, such as acids, or metallic or sharp elements. In public places, this material must comply with the slipperiness requirements of the Spanish Technical Building Code. This document is purely commercial and may not be used in any legal or administrative proceedings, neither as an expert opinion nor as documentary evidence, unless expressly authorized by L'ANTIC COLONIAL, S.A.U.

AC4 NATURAL 11 OAT

## L'ANTIC COLONIAL

| DIMENSIONAL FEATURES   |  |                   |  |  |  |  |
|--|--|-------------------|--|--|--|--|
| Item thickness   | ±0.1 MM  | EN 13329*         |  |  |  |  |
| Length of face   | ±0.5 MM  | EN 13329*         |  |  |  |  |
| Width of face  | ±0.1 MM  | EN 13329*         |  |  |  |  |
| Squareness of the item (q)                                     | ≤0.20 mm   | EN 13329*         |  |  |  |  |
| Straightness of face   | ≤0.30 mm/m   | EN 13329*         |  |  |  |  |
| Flatness of item (f)   | fw,Cóncavo≤0.50% fw,Convexo≤1%/fl,Cóncavo≤0.15% fl,Convexo≤0.20% | EN 13329*         |  |  |  |  |
| Joint between items  | ≤0.20 mm   | EN 13329*         |  |  |  |  |
| Difference in height among items                               | ≤0.15 mm   | EN 13329*         |  |  |  |  |
| Dimensional variations related to changes in relative moisture | ≤0.90 mm   | EN 13329*         |  |  |  |  |
| Uv light fastness  | ≥4   | EN 438-2,16*      |  |  |  |  |
| Punching   | No visible changes   | EN 433*           |  |  |  |  |
| Surface stripping  | ≥1.00 N/mm2  | EN 13329 Anexo D* |  |  |  |  |

|   | LABORATORY TESTS                  |                       |
|---|-----------------------------------|-----------------------|
| Resistance to abrasion  | AC4                               | UNE EN 13329:2000*    |
| Impact resistance   | IC2                               | UNE EN 13329*         |
| Resistance to staining  | Grado 5 (G 1 y 2) y Grado 4 (G 3) | EN 438*               |
| Resistance to cigarette burns                                     | 4                                 | EN 438*               |
| Furniture leg effect  | No damage                         | EN 424*               |
| Castor chair effect   | No damage                         | EN 425*               |
| Swelling in thickness   | ≤12%                              | EN 13329*             |
| Resistance to microscratching                                     | Class 1                           | EN 16094*             |
| Formaldehyde emissions  | E1                                | EN 717*               |
| Slip resistance (pendulum-wet)                                    | CL 1 (29)                         | EN 16165 Anexo C*     |
| Fire resistance   | Cfl-s1                            | EN 13501*             |
| Evaluation of propensity to accumulation of electrostatic charges | ≤2 kV                             | EN 1815*              |
| Heat resistance   | R=0.065 m2 K/W                    | ISO 8302*             |
| Acoustic insulation   | IIC=45dB; STC=45 dB               | ASTM E492 ; ASTM E90* |
| Swelling in thickness   | ≤18%                              | ASTM D 1037*          |
| Slip resistance (dcof)  | 0.60                              | ANSI A137.1*          |
| Critical radiant flux   | Clase 1                           | ASTM E 648*           |
| Smoke density (burning)   | <450 Dmc                          | ASTM E 662*           |
| Density of the board  | 950 ±5 KG/M3                      | UNE EN 323*           |
| Slip resistance (pendulum-dry)                                    | 42                                | EN 16165 Anexo C*     |

|                              | PACKING         |
|------------------------------|-----------------|
| Sales units per box          | 21.27 SQF/CS    |
| Sales units per pallet       | 1106.01 SQF/PAL |
| Sales units per unit         | 2.66 SQF/ST     |
| Sale unit                    | M2              |
| Base unit                    | ST              |
| Sales units per square meter | 1 M2            |
| Net weight                   | 188.31 LB/SQF   |
| Gross weight                 | 193.4 LB/SQF    |

| SPECIAL PIECES |                                    |       |               |                 |                |     |            |                |                |
|----------------|------------------------------------|-------|---------------|-----------------|----------------|-----|------------|----------------|----------------|
| SAP            | Description                        | Group | Boxes         | Pallet          | Units          | SKU | Basic Unit | Net Weight     | Gross weight   |
| 100245561      | IGUALACION NATURAL 1L OAT 4X270X1  | G-155 | 20 PIECES/BOX | 1000 PIECES/PAL | 9.26 PIECES/M2 | -   | -          | 0.7 KG/PIECES  | 0.72 KG/PIECES |
| 100245571      | MAMPERLAN AC4 NATURAL 1L OAT 7X120 | G-163 | 2 PIECES/BOX  | 200 PIECES/PAL  | 11.9 PIECES/M2 | -   | -          | 1.58 KG/PIECES | 1.64 KG/PIECES |
| 100245535      | TRANSICION NATURAL 1L OAT 4X270X1  | G-155 | 20 PIECES/BOX | 1000 PIECES/PAL | 9.26 PIECES/M2 | -   | -          | 0.7 KG/PIECES  | 0.72 KG/PIECES |
| 100245566      | ZOCALO NATURAL 1L OAT 8X220X1,5    | G-107 | 14 PIECES/BOX | 560 PIECES/PAL  | 5.68 PIECES/M2 | -   | -          | 1.8 KG/PIECES  | 1.86 KG/PIECES |





It is advisable to follow the installation and maintenance instructions published by L'ANTIC COLONIAL, S.A.U., observing in any case the legal or regulatory requirements that may exist for each area of use. Do not use aggressive cleaning agents, such as acids, or metallic or sharp elements. In public places, this material must comply with the slipperiness requirements of the Spanish Technical Building Code. This document is purely commercial and may not be used in any legal or administrative proceedings, neither as an expert opinion nor as documentary evidence, unless expressly authorized by L'ANTIC COLONIAL, S.A.U.

06/02/2025