



DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

"We Test Per Your Request"

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

November 17, 2016

VESCOM TEXTILES FOR:
PALLAS TEXTILES
1330 Bellevue Street
Green Bay, WI 54302

Reference: Laboratory Test Report
Lab Identification No. 22536
Invoice No. 53710

Dear Sir or Madam:

One (1) fabric sample, identified as **PATTERN: ASYMETRIC 101794**, was received and tested in accordance with the California Technical Bulletin 117-2013, Section 1, Cover Fabric Test. The results are as follows:

Test Results

Char

10mm	12mm	11mm
------	------	------

The sample submitted **meets** the requirements of the above standard. There were no ignitions or smoldering after 45 minutes on any of the three specimens tested. In addition, none of the three test specimens displayed a char which was greater than 45 mm.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Brian S. Dement

BSD/mr

