



Splendor #11364

Product Specification

Face Construction	Imperial		Metric	
Construction	Stratatec® Patterned Loop			
Face Weight	20	oz/sq yd	678	g/sq m
Gauge	5/64		50.4	rows/10 cm
Stitches per Inch	10.0		39.4	pu/10 cm
Tuft Density	128	tufts/sq in	19.8	tufts/sq cm
Pile Height Average	0.141	inch	3.6	mm
Pile Thickness	0.078	inch	2.0	mm
Pile Density	9,231	oz/cu yd	341.5	kg/cu m
Fiber System	Dynex SD® Nylon (Permanent Stain Resistance)		Kilotex 11.4	
Dye Method	100% Solution Dyed			
Fluorine-Free Soil Protection	Eco-Ensure (Cradle to Cradle™ v3.1 Certified Platinum)			
Primary Tufting Substrate	Synthetic Non-Woven			
Pattern Match	6' W x 71.6" L			

Third Party Environmental Certifications

Product	Recycled Content		Green Label	NSF 140
	Overall	Postconsumer	Plus Certified	SCS Certified
Powerbond® Cushion	15 - 42%	8%	GLP9744	Gold
Powerbond® Medfloor®	15 - 42%	8%	GLP9744	

Powerbond® Cushion RS® CERTIFIED asthma & allergy friendly®



Product Testing/Information

Antimicrobial Chemicals	No antimicrobials (EPA Registered pesticides) added to product (ASTM E2471-05)
Electrostatic Propensity	≤3.0 kV (AATCC 134); Permanent Conductive Fiber
Surface Flammability	Passes CPSC FF 1-70 (ASTM D-2859)
Flooring Radiant Panel	Class 1 (mean average CRF: 0.45 w/sq cm or higher) (ASTM E-648)
Smoke Generation	Less than 450 (ASTM E-662)
Colorfastness to Light	≥ 4 after 100 hours (AATCC 16E)
Soil Protection	Application Rate: 2% of Face Weight
Stain Resistance	≥ 8 (AATCC 175-08 Stain Resistance Pile Floor Coverings)

Installation Methods

Peel and Stick	RS Adhesive System - Full Coverage Peel & Stick
Wet Spread	Backing specific Tarkett Adhesives

Product Notes

- Specifications are subject to nominal manufacturing variances. Material supply and/or manufacturing processes may necessitate changes without notice. Colors may vary slightly from dye lot to dye lot.
- U.S. Patent numbers: 4,849,267; 6,406,574, US 9,988,760 B2
- Chair pads are recommended for optimum textural performance. Absent the use of chair pads, more intensive maintenance will be required for areas in direct contact with chair caster traffic, and some degree of appearance change is to be expected.

Tarkett North America

Technical Services Department
1104 Willowdale Road NW
Dalton, GA 30721
800.248.2878

www.tarkett.com

© 2024 Tarkett USA Inc. 2/2024



IMPERIAL	METRIC	TEST METHOD
----------	--------	-------------

Warranty: Lifetime limited warranty against excessive surface wear, static, delamination, edge ravel, zippering, backing resiliency loss & stain resistance.

Powerbond® Cushion

Total Minimum Recycled Content	23.3%				
Pre-Consumer	14.5%				
Postconsumer	8.8%				
Product Size	6 ft.				
Cushion	Closed Cell Cushion				
Heterogeneous Construction	No Delamination per ASTM D-3936				
Cushion Weight	35.5 oz/sq yd	1203	g/sq m	ASTM D1667	
Cushion Density	18.5 lbs/cu ft	296	kg/cu m	ASTM D1667	
Cushion Thickness	0.156 inch	4.0	mm	ASTM D1667	
Total Weight with RS / Non-RS	81.0 78.7 oz/sq yd +/-5%	2747	2669	g/sq m	
Compression Set	Max. 10%			ASTM D1667	
Compression Deflection	7 Min. 25 max lbs/sq inch @ 25%	492	1758	g/sq cm	ASTM D1667

Powerbond Medfloor®

Total Minimum Recycled Content	23.3%				
Pre-Consumer	14.5%				
Postconsumer	8.8%				
Product Size	6 ft.				
Cushion	Medfloor				
Heterogeneous Construction	No Delamination per ASTM D-3936				
Cushion Weight	37 oz/sq yd	1254	g/sq m	ASTM D1667	
Cushion Density	30 lbs/cu ft	481	kg/cu m	ASTM D1667	
Cushion Thickness	0.085 inch	2.2	mm	ASTM D1667	
Total Weight	80.2 oz/sq yd +/-5%	2720	g/sq m		
Compression Set	Max. 10%			ASTM D1667	
Compression Deflection	29 lbs/sq inch @ 25%	2039	g/sq cm	ASTM D1667	