



## Time Abstraction #G0095

## Product Specification

Face Construction	Imperial		Metric		
Construction	Tufted Patterned Loop				
Face Weight	21	oz/sq yd	711.9	g/sq m	
Gauge	1/10		39.4	rows/10 cm	
Stitches per Inch	10.0		39.4	pu/10 cm	
Tuft Density	100	tufts/sq in	15.5	tufts/sq cm	
Pile Height Average	0.172	inch	4.4	mm	
Pile Thickness	0.131	inch	3.3	mm	
Pile Density	5,771	oz/cu yd	213.5	kg/cu m	Kilotex 6.2
Fiber System	Dynex SD® Nylon (Permanent Stain Resistance)				
Dye Method	Solution Dyed				
Fluorine-Free Soil Protection	Eco-Ensure (Cradle to Cradle™ v3.1 Certified Platinum)				
Primary Tufting Substrate	Synthetic Non-Woven				
Pattern Match	72" W x 72" L				

### Third Party Environmental Certifications

Product	Recycled Content		Green Label	NSF 140
	Overall	Postconsumer	Plus Certified	SCS Certified
Powerbond® Cushion	15 - 42%	8%	GLP9744	Gold

Powerbond® Cushion RS® CERTIFIED asthma & allergy friendly®



### Product Testing/Information

Antimicrobial Chemicals	No antimicrobials (EPA Registered pesticides) added to product (ASTM E2471-05)
Electrostatic Propensity	≤3.0 kV (AATCC 134); Permanent Conductive Fiber
Surface Flammability	Passes CPSC FF 1-70 (ASTM D-2859)
Flooring Radiant Panel	Class 1 (mean average CRF: 0.45 w/sq cm or higher) (ASTM E-648)
Smoke Generation	Less than 450 (ASTM E-662)
Colorfastness to Light	≥ 4 after 100 hours (AATCC 16E)
Soil Protection	Application Rate: 2% of Face Weight
Stain Resistance	≥ 8 (AATCC 175-08 Stain Resistance Pile Floor Coverings)

### Installation Methods

Peel and Stick	RS Adhesive System - Full Coverage Peel & Stick
Wet Spread	Backing specific Tarkett Adhesives

### Product Notes

- Specifications are subject to nominal manufacturing variances. Material supply and/or manufacturing processes may necessitate changes without notice. Colors may vary slightly from dye lot to dye lot.
- U.S. Patent numbers: 4,849,267; 6,406,574, US 9,988,760 B2
- Chair pads are recommended for optimum textural performance. Absent the use of chair pads, more intensive maintenance will be required for areas in direct contact with chair caster traffic, and some degree of appearance change is to be expected.

### Tarkett North America

Technical Services Department  
1104 Willowdale Road NW  
Dalton, GA 30721  
800.248.2878

[www.tarkett.com](http://www.tarkett.com)

© 2024 Tarkett USA Inc. 9/2024



IMPERIAL

METRIC

TEST METHOD

Warranty: Lifetime limited warranty against excessive surface wear, static, delamination, edge ravel, zippering, backing resiliency loss & stain resistance.

**Powerbond® Cushion**

Total Minimum Recycled Content	23.7%					
Pre-Consumer	15.0%					
Postconsumer	8.7%					
Product Size	6 ft.					
Cushion	Closed Cell Cushion					
Heterogeneous Construction	No Delamination per ASTM D-3936					
Cushion Weight	35.5	oz/sq yd		1203	g/sq m	ASTM D1667
Cushion Density	18.5	lbs/cu ft		296	kg/cu m	ASTM D1667
Cushion Thickness	0.156	inch		4.0	mm	ASTM D1667
Total Weight with RS / Non-RS	82.0	79.7	oz/sq yd +/-5%	2781	2703	g/sq m
Compression Set	Max. 10%					ASTM D1667
Compression Deflection	7 Min.	25 max	lbs/sq inch @ 25%	492	1758	g/sq cm