

Assertive Rib #04838

Product Specification

Face Construction	Imperial		Metric					
Construction	Textured I	Textured Loop						
Face Weight	27	oz/sq yd	915.3	g/sq m				
Gauge	1/13		50.4	rows/10 cm				
Stitches per Inch	9.0		35.4	pu/10 cm				
Tuft Density	115.2	tufts/sq in	17.9	tufts/sq cm				
Pile Height Average	0.117	inch	3.0	mm				
Pile Thickness	0.106	inch	2.7	mm				
Pile Density	9,170	oz/cu yd	339.3	kg/cu m	Kilotex 18.4			
Fiber System	TDX® Nylon							
Dye Method	100% Solution Dyed							
Fluorine-Free Soil Protection	Eco-Ensure (Cradle to Cradle™ v3.1 Certified Platinum)							
Primary Tufting Substrate	Synthetic Non-Woven							
Pattern Match	Not Requi	red						

Third Party Environmental Certifications

Product	Recycled Content		Green Label	NSF 140	Cradle to Cradle
	Overall	Postconsumer	Plus Certified	SCS Certified	Certified™ v3.1
ethos® Modular with Omnicoat Technology®	56 - 79%	30%	GLP8320	Gold	Silver
Flex-Aire Modular® Cushion	28 - 46%	22%	GLP6558	Gold	СМ
					CERTIFIED
					cradletocradle
					SILVER

Product Testing/Information			
Antimicrobial Chemicals	No antimicrobials (EPA Registered pesticides) added to product (ASTM E2471-05)		
Electrostatic Propensity	≤3.0 kV (AATCC 134); Permanent Conductive Fiber		
Surface Flammability	Passes CPSC FF 1-70 (ASTM D-2859)		
Flooring Radiant Panel	Class 1 (mean average CRF: 0.45 w/sq cm or higher) (ASTM E-648)		
Smoke Generation	Less than 450 (ASTM E-662)		
Colorfastness to Light	≥ 4 after 100 hours (AATCC 16E)		
Soil Protection	Application Rate: 2% of Face Weight		
Installation Methods			
Peel and Stick	RS Adhesive System - Full Coverage Peel & Stick		
Wet Spread	Backing specific Tarkett Adhesives		
Installation Method	24"x 24" Quarter Turn, Vertical Ashlar; 18"x 36" and 9"x 36" Vertical Ashlar, Herringbone		

Product Notes

- 1. Specifications are subject to nominal manufacturing variances. Material supply and/or manufacturing processes may necessitate changes without notice. Colors may vary slightly from dye lot to dye lot.
- 2. U.S. Patent numbers: 4,849,267; 6,406,574, US 9,988,760 B2
- 3. Chair pads are recommended for optimum textural performance. Absent the use of chair pads, more intensive maintenance will be required for areas in direct contact with chair caster traffic, and some degree of appearance change is to be expected.

Tarkett North America

Technical Services Department 1104 Willowdale Road NW Dalton, GA 30721 800.248.2878

www.tarkett.com



IMPERIAL **METRIC** TEST METHOD Warranty: Lifetime limited warranty against excessive surface wear, static, delamination, edge ravel, zippering, backing resiliency loss. ethos® Modular with Omnicoat Technology® **Total Minimum Recycled Content** 58.4% Pre-Consumer 28.3% Postconsumer 30.1% Product Size 24" x 24" Tile (9" x 36" and 18" x 36" also available) Secondary Backing 50% Recycled Content Fiberglass Reinforced Sealant Intermediate Layer No Delamination per ASTM D-3936 **Product Construction** Secondary Backing Density 65.0 lbs/cu ft 1041 kg/cu m Secondary Backing Thickness 0.050 inch 1.3 mm Total Weight 104.9 oz/sq yd +/-5% 3555.8 g/sq m Flex-Aire Modular® Cushion **Total Minimum Recycled Content** 28.1% Pre-Consumer 5.6% Postconsumer 22.5% Product Size 24" x 24" Tile (9" x 36" and 18" x 36" also available) Secondary Backing Fiberglass Reinforced Composite Closed Cell Cushion Intermediate Layer Fiberglass Reinforced Sealant **Product Construction** No Delamination per ASTM D-3936 **Cushion Weight** 35.5 oz/sq yd 1203 **ASTM D1667** g/sq m **Cushion Density** 18.5 lbs/cu ft 296 **ASTM D1667** kg/cu m **Cushion Thickness** 0.156 4.0 **ASTM D1667** inch mm Total Weight with RS / Non-RS 4276 126.1 124.7 oz/sq yd +/-5% 4229 g/sq m Compression Set Max. 10% **ASTM D1667** Compression Deflection 5 Min. 25 max lbs/sq inch @ 25% 352 1758 **ASTM D1667** g/sq cm

800.248.2878 www.tarkett.com © 2024 Tarkett USA Inc. 2/2024