

Attract #A0044

Product Specification

Face Construction	Imperial		Metric			
Construction	Tufted Pat	tterned Loop				
Face Weight	20	oz/sq yd	678	g/sq m		
Gauge	1/10		39.4	rows/10 cm		
Stitches per Inch	10.0		39.4	pu/10 cm		
Tuft Density	100	tufts/sq in	15.5	tufts/sq cm		
Pile Height Average	0.172	inch	4.4	mm		
Pile Thickness	0.112	inch	2.8	mm		
Pile Density	6,429	oz/cu yd	237.9	kg/cu m	Kilotex 9.3	
Fiber System	Dynex SD® Nylon (Permanent Stain Resistance)					
Dye Method	100% Solution Dyed					
Fluorine-Free Soil Protection	Eco-Ensure (Cradle to Cradle™ v3.1 Certified Platinum)					
Primary Tufting Substrate	Synthetic Non-Woven					
Pattern Match	Not Requi	red				

Third Party Environmental Certifications

SCS Certified Gold	Certified™ v3.1 Silver
Gold	Silver
Gold	CERTIFIED
	cradletocradle
	Gold

Product Testing/Information			
Antimicrobial Chemicals	No antimicrobials (EPA Registered pesticides) added to product (ASTM E2471-05)		
Electrostatic Propensity	≤3.0 kV (AATCC 134); Permanent Conductive Fiber		
Surface Flammability	Passes CPSC FF 1-70 (ASTM D-2859)		
Flooring Radiant Panel	Class 1 (mean average CRF: 0.45 w/sq cm or higher) (ASTM E-648)		
Smoke Generation	Less than 450 (ASTM E-662)		
Colorfastness to Light	≥ 4 after 100 hours (AATCC 16E)		
Soil Protection	Application Rate: 2% of Face Weight		
Stain Resistance	> 8 (AATCC 175-08 Stain Resistance Pile Floor Coverings)		

Installation Methods

Peel and Stick	RS Adhesive System - Full Coverage Peel & Stick
Wet Spread	Backing specific Tarkett Adhesives
Installation Method	18" x 36" Herringbone, Vertical Ashlar

Product Notes

- 1. Specifications are subject to nominal manufacturing variances. Material supply and/or manufacturing processes may necessitate changes without notice. Colors may vary slightly from dye lot to dye lot.
- 2. U.S. Patent numbers: 4,849,267; 6,406,574, US 9,988,760 B2
- 3. Chair pads are recommended for optimum textural performance. Absent the use of chair pads, more intensive maintenance will be required for areas in direct contact with chair caster traffic, and some degree of appearance change is to be expected.

Tarkett North America

Technical Services Department 1104 Willowdale Road NW Dalton, GA 30721 800.248.2878

<u>www.tarkett.com</u> © 2024 Tarkett USA Inc. 2/2024



	IMPERIAL			METRIC		TEST METHOD
Varranty: Lifetime limited warrar	nty agains	st excessive surface wear,	static, d	lelaminat	ion, edge r	avel, zippering, backing resilienc
thos® Modular with Omnicoat T	echnolo	gy®				
Total Minimum Recycled Content	67.3%					
Pre-Consumer	35.0%					
Postconsumer	32.3%					
Product Size	18" x 36	6" Tile				
Secondary Backing	50% Re	cycled Content				
ntermediate Layer	Fibergla	ass Reinforced Sealant				
Product Construction		amination per ASTM D-3936				
Secondary Backing Density	65.0	lbs/cu ft		1041	kg/cu m	
Secondary Backing Thickness	0.050	inch		1.3	mm	
Total Weight	97.9	oz/sq yd +/-5%		3318.5	g/sq m	
lex-Aire Modular® Cushion						
otal Minimum Recycled Content	33.6%					
Pre-Consumer	9.8%					
Postconsumer	23.8%					
Product Size	18" x 36	S" Tile				
Secondary Backing		ass Reinforced Composite Clo	nead Ca	ll Cuchion	1	
ntermediate Layer		ass Reinforced Sealant	Jaeu Ce	ii Cusiiioi	Į.	
Product Construction		amination per ASTM D-3936				
Cushion Weight	35.5	oz/sq yd		1203	g/sq m	ASTM D1667
Cushion Density	18.5	lbs/cu ft		296	kg/cu m	ASTM D1667
Cushion Thickness	0.156	inch		4.0	mm	ASTM D1667
Total Weight with RS / Non-RS	119.1	117.7 oz/sq yd +/-5%	4039	3991	g/sq m	ASTIN D1007
Compression Set	Max. 10		4000	3331	g/sq III	ASTM D1667
Compression Deflection	5 Min.	25 max lbs/sq inch @ 25%	352	1758	g/sq cm	ASTM D1667
Compression Deflection	J WIIII.	25 max ibs/sq men @ 25%	332	1730	g/sq cili	ASTIN D 1007
_						

800.248.2878 www.tarkett.com © 2024 Tarkett USA Inc. 2/2024