

noraplan environcare ed

Electrostatically dissipative (ESD) rubber sheet flooring in a design combining a changing base color of three harmoniously matched color components and characteristic granules with a smooth surface. Provides optimum ESD protection for electronic devices and equipment.



Product Construction Specifications

Product: noraplan environcare™ ed 3 mm resilient floor covering, Article 1523

Material Composition: nora® vulcanized rubber compound 948 with environmentally compatible color pigments that are free of toxic heavy metals like lead, cadmium, or mercury

Material Size: 15 m by 1.22 m (~49.21 ft by 48 in)

Thickness: 3 mm (~0.12 in)

Dimensional Stability: Meets requirements

Construction: Homogeneous rubber compound with a random scattered design

Colors: 14 Standard

Surface: Smooth

Performance Standards

| | |
|---|--|
| Flammability (E648/NFPA 253): ≥ 0.45 watts/sq cm for Class 1 is required | NBSIR 75 950, 1.0 |
| Smoke Density (ASTM E662): < 450 is required | NBS, 352 (flaming) and 342 (non-flaming) |
| Slip Resistance (ASTM D2047): ≥ 0.5 is required | Static coefficient of friction, Neolite dry 0.92 Neolite wet 0.89 |
| Bacteria Resistance (ASTM E2180/ASTM G21): | Resistant to bacteria, fungi, and micro-organism activity |
| Sound Absorption (ASTM E2179/ISO 10140-3): | ΔIIC 10, ΔLw 10 dB (compare only Δ values) |
| Hardness (ASTM D2240): ≥ 85 is required | Shore type A, 92 |
| Static Load (ASTM F970): ≤ 0.005 in with 250 lbs is required | Residual compression of 0.003 in with 800 lbs |
| Rolling Load Limit (ASTM F2753): | ≤ 550 lbs/sq in; no forklift traffic |
| Abrasion Resistance (ASTM D3389): ≤ 0.035 oz (1.0 g) is required | 1.1 lbs (500 g) load on H-18 wheel with 1000 cycles, 0.003 oz (0.09 g) weight loss |
| Oil & Grease Resistance (ISO 26987): | Yes |
| Static Generation (ANSI ESD S97.2): | < 20 Volts |
| Decay Time (FTM 101 C 4046): | < 0.25 (sec) |
| Conductivity (ASTM F150): | 10 ⁶ < 10 ⁹ (ohms) |

Health + Environmental Specifications

Indoor Air Quality: GREENGUARD Gold Certified for low VOC emissions in compliance with CDPH 01350

Discloser of Environmental Impact: Environmental Product Declarations (EPDs)

Disclosure of Product Ingredients: Health Product Declarations (HPDs)

LEED v4: Contributes to multiple IEQ and MR credits

Material Composition: Free of added formaldehyde, heavy metals and ortho-phthalates, fluorinated chemicals (PFAS), and halogenated flame retardants

Production Plant Certifications: ISO 9001:2000, ISO 14001

Installation

Site Conditions: The installation area must be fully enclosed, weather tight, and climate controlled between 63°F and 75°F and 40% to 60% ambient relative humidity (RH) for at least 48 hours prior, during and 72 hours after installation.

Adhesive:

- Absorptive substrates: use nora® ED MR90™ or nora dryfix™ ed adhesives
- Nonabsorptive substrates: use nora dryfix ed
- Must use copper strip for every 2,500 square feet; all areas not in direct contact with the surrounding flooring will require additional copper strip

Unique Characteristics:

- Good for heavy traffic
- Superior footfall sound absorption
- Superior slip resistance
- High fire-retardant properties
- Monolithic seamless installation with coordinating weld
- Welding not required, unless specified

For complete installation instructions refer to the nora Installation Instructions.

Care and Cleaning

No finishes/coatings or harsh chemicals necessary. A post-installation cleaning must be performed before the area is occupied. Refer to the nora Maintenance Guidelines.

Wheel Types

No metal or hard plastic wheels, the shape of the contact surface of wheels must be flat with round edges. The shore hardness must be Type A ≤ 90.

Storage

nora flooring can be stored within a temperature range of -5°F (-21°C) to 120°F (49°C) under the following conditions: Pallets must remain intact with sheet goods standing on end, undamaged, not be stacked, be in a permanently dry environment, and with no direct sunlight. However, all adhesives and cold weld must remain at room temperature without freezing.

Warranty

Limited 10-year conductivity warranty and 15-year warranty. Refer to the nora Limited Warranty - Americas.

Current nora Installation Instructions, Guide Specifications, Maintenance Guidelines, and Limited Warranties, can be found at www.nora.com.

nora®, norament®, and noraplan® are trademarks owned by nora systems GmbH and registered in the United States, Canada, and other countries. Cradle to Cradle Certified® is a registered trademark of the Cradle to Cradle Products Innovation Institute. Other labels used here are trademarks of their respective owners.

Updated: April 2024