

FIORANO USA  
VEIN

STONESOURCE

# FIORANO USA VEIN



/ SILVER p.6



/ CORDA p.12



/ CENERE p.26



/ ANTRACITE p.34




/ AVORIO p.20

colors / matte & semi-  
polsihed


/ AVORIO



/ SILVER




/ CORDA



/ CENERE



/ ANTRACITE





# FIORANO USA VEIN

FIORANO USA VEIN is a strong, sophisticated porcelain that is designed to out-perform all expectations. Available in five colors and three sizes, is perfect for any room in your home or business.







FIORANO USA VEIN / AVORIO









FIORANO USA VEIN / SILVER





6"x24" / SILVER





FIORANO USA VEIN / CORDA









FIORANO USA VEIN / CENERE









FIORANO USA VEIN / ANTRACITE





12"x24" . 6"x24" / ANTRACITE



# SIZES & SHADE VARIATION

## sizes:

12"x12"



1095146 Corda  
1095143 Avorio  
1095145 Cenere  
1095147 Silver  
1095144 Antracite

12"x24"



1095163 Corda  
1095160 Avorio  
1095162 Cenere  
1095164 Silver  
1095161 Antracite

6"x24"

Rectified



1095223 Corda  
1095220 Avorio  
1095222 Cenere  
1095224 Silver  
1095221 Antracite

Colors shown may vary from actual product.  
Final selection should be made from actual product samples.


11.54"x23.19" Rectified, Semi Polished



1095263 Corda  
1095260 Avorio  
1095262 Cenere  
1095264 Silver  
1095261 Antracite

## mosaics & trim pieces:

Mosaic 12"x12"



1095173 Corda  
1095170 Avorio  
1095172 Cenere  
1095174 Silver  
1095171 Antracite

3"x12"

Bullnose




1095168 Corda  
1095165 Avorio  
1095167 Cenere  
1095169 Silver  
1095166 Antracite

6"x12" Cove Base \*special order only




1095178 Corda  
1095175 Avorio  
1095177 Cenere  
1095179 Silver  
1095176 Antracite




V1

UNIFORM APPEARANCE  
Differences among pieces from the same production run are minimal.




V2

SLIGHT VARIATION  
Clearly distinguishable differences in texture and/or pattern with similar colors.



V3

MODERATE VARIATION  
While the colors present on a single piece of tile will be indicative of the colors to be expected on the other tiles, the amount of colors on each piece will vary significantly.






V4

SUBSTANTIAL VARIATION  
Random color differences from tile to tile, so that one tile may have totally different colors from that on other tiles. Thus, the final installation will be unique.



# Technical Specifications

This product meets or exceeds all standards described in ANSI A137.1 & A137.3. Este product cumple o exceed todos los estandares de ANSI A137.1 & A137.3.

	SPECS	TEST METHOD	INDUSTRY STANDARD	MILE®stone VALUES	
	WATER ABSORPTION	ASTM C373	≤0.5%	≤0.5%	
	SURFACE WEAR RESISTANCE	ANSI A137.1	Surface Wear-resistance properties of glazed vitreous and porcelain tiles.	ALL RESIDENTIAL / COMMERCIAL	
	CHEMICAL RESISTANCE	ASTM C650	A tile sample is placed in continuous contact with a variety of chemicals for 24 hours. Sample must show no visible defects.	NOT AFFECTED	
	D.C.O.F. AcuTest®	ANSI A326.3	INDOOR ≥0.42 WET	≥0.42 WET	
			OUTDOOR >0.55 WET	>0.55 WET 2CM & GRIP	
	STAIN RESISTANCE	ASTM C1378	Surfaces are exposed to staining agents for 24 hours followed by four cleaning procedures. Results are recorded post cleaning.	NOT AFFECTED	
	BREAKING STRENGTH GAUGED PORCELAIN	ASTM C1505	≥175 lbf	≥200 lbf	
	BREAKING STRENGTH	ASTM C648	≥275 lbf	≥300 lbf	
	BREAKING STRENGTH OUTDOOR 2CM	ASTM 1505	2000 lbf (10.9 kN)	≥2500 lbf	
	RESISTANCE TO FREEZE	ASTM C1026	A tile sample is subjected to repeated processes of freezing and thawing. Sample must show no visible defects.	RESISTANT	
	WARPAGE EDGE	ASTM C485	±0.40% or ±0.05 in ( ±1.8 mm)	± 0.40%	Rectified
	WARPAGE DIAGONAL	ASTM C485	±0.40% or ±0.07 in (±1.8 mm)	± 0.40%	Rectified
	WEDGING	ASTM C502	±0.25% or ±0.03 in (±0.8 mm)	± 0.25%	Rectified
	WARPAGE EDGE	ASTM C485	±0.50% or ±0.07 in (±1.8 mm)	± 0.50%	Calibrated
	WARPAGE DIAGONAL	ASTM C485	±0.50% or ±0.07 in (±1.8 mm)	± 0.50%	Calibrated
	WEDGING	ASTM C502	±0.50% or ±0.08 in (±2.0 mm)	± 0.50%	Calibrated
	THICKNESS	ASTM C499	Range: ± 0.04 in	≤0.04 in	

• Due to the inherent nature of fired porcelain tile, it is important to note that the coefficient of friction may vary within and between product runs.



