

PALERMO
LIMESTONE 3D

STONESOURCE

Wall: GRIGIO Design Natural 12"x24" Rectified



GRIGIO Design Natural 12"x24" Rectified

PALERMO LIMESTONE 3D

COLORED BODY FINE PORCELAIN STONEWARE

PRODUCT INFORMATION

BIANCO



DESIGN 12"x24" Rectified

Thickness: **9.5mm**

Finishes: **Natural**



MURETTO 12"x24" Rectified

Thickness: **9.5mm**

Finishes: **Natural**

PALERMO LIMESTONE 3D

COLORED BODY FINE PORCELAIN STONEWARE

PRODUCT INFORMATION

AVORIO



DESIGN 12"x24" Rectified

Thickness: **9.5mm**

Finishes: **Natural**



MURETTO 12"x24" Rectified

Thickness: **9.5mm**

Finishes: **Natural**

PALERMO Limestone 3D

COLORED BODY FINE PORCELAIN STONEWARE

PRODUCT INFORMATION

TORTORA



DESIGN 12"x24" Rectified

Thickness: **9.5mm**

Finishes: **Natural**



MURETTO 12"x24" Rectified

Thickness: **9.5mm**

Finishes: **Natural**

PALERMO LIMESTONE 3D

COLORED BODY FINE PORCELAIN STONEWARE

PRODUCT INFORMATION

PERLA



DESIGN 12"x24" Rectified

Thickness: 9.5mm

Finishes: **Natural**



MURETTO 12"x24" Rectified

Thickness: 9.5mm

Finishes: **Natural**

PALERMO Limestone 3D

COLORED BODY FINE PORCELAIN STONEWARE

PRODUCT INFORMATION

GRIGIO



DESIGN 12"x24" Rectified

Thickness: **9.5mm**

Finishes: **Natural**



MURETTO 12"x24" Rectified

Thickness: **9.5mm**

Finishes: **Natural**

PALERMO LIMESTONE 3D

COLORED BODY FINE PORCELAIN STONEWARE

PACKAGING

SIZES	PCS/BOX	SQMT/BOX	KGS/BOX	BOXES/PALLET	SQMT/PALLET	KGS/PALLET	PALLET SIZE (CM)
DESIGN 12"x24" Rectified	6	1.080	21.50	40	43.20	860	120x80x75
MURETTO 12"x24" Rectified	6	1.080	21.50	40	43.20	860	120x80x75

PALERMO LIMESTONE 3D

COLORED BODY FINE PORCELAIN STONEWARE

TECHNICAL CHARACTERISTICS

CLASSIFICATION IN ACCORDANCE WITH CEN/ISO STANDARDS B1A EN 14411 - ISO 13006

TECHNICAL CHARACTERISTICS	NORM	REQUIRED VALUE	MEAN VALUE		USA TEST	MEAN VALUE
Length and Width	ISO 10545-2	±0.6% (±2.00 mm)	In Accordance		ASTM C499 ASTM C485 ASTM C502	In Accordance
Thickness		±5% (±0.5 mm)				
Warpages of Edges		±0.5% (±1.5 mm)				
Wedging		±0.5% (±2.00 mm)				
Flatness		±0.5% (±2.00 mm)				
Water Absorption	ISO 10545-3	≤ 0.5%	In Accordance		ASTM C373	In Accordance
Bending Strength	ISO 10545-4	≥ 35N/mm ²	In Accordance		ASTM C648 250 LBS or greater	In Accordance
Linear Thermal Expansion Between 20° and 100° C	ISO 10545-8	According to builder's specification	≈ 7X10 ⁻⁶ C ⁻¹			
Thermal Shock Resistance	ISO 10545-9	Request	Resistant			
Frost Resistance	ISO 10545-12	Request	Resistant		ASTM C1026	In Accordance
Resistance to Chemical Attack	ISO 10545-13	According to builder's specification	Resistant		ASTM C650	In Accordance
Colors Resistance to Light	DIN 51094	No alteration	In Accordance			
Stain Resistance	ISO 10545-14	≥ Class 3 Test mehtod available	In Accordance			
Slippage Resistance	DIN 51130	9 ≤ R ≤ 13	VELVET	R11	ASTM C-1028 * COF ≥ 0.6 Dry ≥ 0.6 Wet	-
	DIN 51097	A,B,C	VELVET	-	DCOF ANSI 137.1-2012 ≥ 0.42 Wet	-



STONESOURCE