

# CITY PROPER

EC1

Modular Tile

## Construction

Tufted, Tip Shear

## Tile Size

50 cm x 50 cm (19.7" x 19.7")

## Yarn Type

Universal Fibers® Solution-Dyed Nylon

## Stain Resist / Soil Release

StainSmart®

## Dye Method

Solution Dyed

## Tufted Face Weight

22.0 oz/yd<sup>2</sup> (745.9 g/m<sup>2</sup>)

## Gauge

1/12

## Stitches Per Inch

11.8

## Tufts

142.0/in<sup>2</sup> (2,199/100 cm<sup>2</sup>)

## Finished Pile Thickness

0.128" (3.25 mm)

## Average Density (Finished)

5,878

## Standard Backing

PVC-Free WellBAC® Comfort Plus Cushion

Available with TractionBack®

## Recycled Content by Total Weight

Standard Backing NSF 140 Gold: 51.5% Pre-Consumer, 0.0% Post-Consumer  
NSF 140 Platinum Backing Option: 42.5% Pre-Consumer, 9.0% Post-Consumer

## Embodied Carbon

14.1 (kg CO<sub>2</sub>e)/m<sup>2</sup>

## Nominal Total Thickness

0.465" (11.8 mm)

## Nominal Total Weight

113.0 oz/yd<sup>2</sup> (3,831 g/m<sup>2</sup>)

## Flammability (Radiant Panel

ASTM-E-648)

≥ 0.45 (Class I)

## Smoke Density (NFPA-258-T or

ASTM-E-662)

≤ 450

## Methenamine Pill Test (CPSC FF-1-70 or ASTM D 2859

Self-Extinguishing

## Lightfastness (AATCC 16E)

≥ 4.0 at 80 Hours

## Crocking (AATCC 165)

≥ 4.0 Wet or Dry

## Static Electricity (AATCC-134) 20% R.H., 70° F.

≤ 3.5 KV, Permanent Conductive Fiber

## Texture Appearance Retention Rating (TARR)

Heavy Traffic End-Use Applications

## Recommended Maintenance

MilliCare® Textile and Carpet Care Service Network

## Indoor Air Quality—CRI Green Label Plus™

GLP7205, Carpet Category 13X

## Recommended Installation Method(s)

Monolithic

## WARRANTIES

Lifetime Face Fiber Wear

Lifetime Antistatic

Lifetime Floor Compatibility

Lifetime Color Pattern Permanency

Lifetime Floor Release

Lifetime Cushion Resiliency

Lifetime Moisture Resistance

Lifetime Delamination of Backing Lifetime

Staining/Soiling (StainSmart®) Lifetime

Dimensional Stability

Lifetime Tuft Bind

Lifetime Edge Ravel

Flammability



Declare.



This cushion-back carpet tile product is covered by one or more patents, published applications and/or patents pending. Specifications are subject to normal manufacturing tolerances and may be changed without prior notice. Copies of actual test results are available upon request.