Milliken

TEXTURED SKY

Rainmaker - Eco Low Embodied Carbon Version

Modular Tile

Construction

Tufted, Textured Loop

Tile Size

50 cm x 50 cm (19.7" x 19.7") 25 cm x 1 m (9.84" x 39.4")

Yarn Type

Universal Fibers® Solution-Dyed Recycled Nylon

Stain Resist / Soil Release

StainSmart®

Dye Method

Solution Dyed

Tufted Face Weight

 $28.0 \text{ oz/yd}^2 (949.4 \text{ g/m}^2)$

Gauge

1/12

Stitches Per Inch

10.4

Tufts

124.8/in² (1,933/100 cm²)

Finished Pile Thickness

0.120" (3.05 mm)

Average Density (Finished)

8,229

Standard Backing

PVC-Free WellBAC® Comfort Plus Cushion

Available with TractionBack®

Recycled Content by Total Weight

Standard Backing NSF 140 Gold: 57.7% Pre-Consumer, 0.0% Post-Consumer NSF 140 Platinum Backing Option: 49.1% Pre-Consumer, 8.7% Post-Consumer

Embodied Carbon

 $8.7 (kg CO_2 e)/m^2$

Nominal Total Thickness

0.380" (9.7 mm)

Nominal Total Weight

 $119.0 \text{ oz/yd}^2 (4,035 \text{ g/m}^2)$

Flammability (Radiant Panel ASTM-E-648)

≥ 0.45 (Class I)

Smoke Density (NFPA-258-T or ASTM-E-662)

≤ 450

Methenamine Pill Test (CPSC FF-1-70 or ASTM D 2859

Self-Extinguishing

Lightfastness (AATCC 16E)

≥ 4.0 at 80 Hours

Crocking (AATCC 165)

 \geq 4.0 Wet or Dry

Static Electricity (AATCC-134) 20% R.H.,70° F.

≤ 3.5 KV, Permanent Conductive Fiber

Texture Appearance Retention Rating (TARR)

Heavy Traffic End-Use Applications

Recommended Maintenance

MilliCare® Textile and Carpet Care Service Network

Indoor Air Quality—CRI Green Label Plus™

GLP7205, Carpet Category 13X

Recommended Installation Method(s)

Monolithic, Ashlar, Planks

WARRANTIES

Lifetime Face Fiber Wear Lifetime Antistatic Lifetime Floor Compatibility Lifetime Color Pattern Permanency Lifetime Floor Release Lifetime Cushion Resiliency Lifetime Moisture Resistance Lifetime Delamination of Backing Lifetime Staining/Soiling (StainSmart®) Lifetime Dimensional Stability

Lifetime Tuft Bind Lifetime Edge Ravel Flammability













This cushion-back carpet tile product is covered by one or more patents, published applications and/ or patents pending. Specifications are subject to normal manufacturing tolerances and may be changed without prior notice. Copies of actual test results are available upon request.