

COLOR THESIS

Artwork

Modular Tile

Construction

Tufted, Textured Loop, Tip Shear

Tile Size

1 m x 1 m (39.4" x 39.4")
 50 cm x 1 m (19.7" x 39.4")
 25 cm x 1 m (9.84" x 39.4")

Yarn Type

Milliken-Certified WearOn® Nylon

Stain Resist / Soil Release

StainSmart®

Dye Method

PrintWorks™ Precision Dyeing

Tufted Face Weight

32.0 oz/yd² (1085.0 g/m²)

Gauge

5/64

Stitches Per Inch

10.8

Tufts

138.0/in² (2,137/100 cm²)

Finished Pile Thickness

0.107" (2.72 mm)

Average Density (Finished)

9,117

Standard Backing

PVC-Free WellBAC® Comfort Plus Cushion
 Available with TractionBack®

Recycled Content by Total Weight

Standard Backing NSF 140 Gold:
 40.0% Pre-Consumer, 0.0% Post-Consumer
 NSF 140 Platinum Backing Option:
 32.2% Pre-Consumer, 8.1% Post-Consumer

Embodied Carbon

21.0 (kg CO₂e)/m²

Nominal Total Thickness

0.380" (9.7 mm)

Nominal Total Weight

116.0 oz/yd² (3,933 g/m²)

Flammability (Radiant Panel

ASTM-E-648)
 ≥ 0.45 (Class I)

Smoke Density (NFPA-258-T or

ASTM-E-662)
 ≤ 450

Methenamine Pill Test (CPSC FF-1-70 or ASTM D 2859

Self-Extinguishing

Lightfastness (AATCC 16E)

≥ 4.0 at 80 Hours

Crocking (AATCC 165)

≥ 4.0 Wet or Dry

Static Electricity (AATCC-134) 20% R.H., 70° F.

≤ 3.5 KV, Permanent Conductive Fiber

Texture Appearance Retention Rating (TARR)

Severe Traffic End-Use Applications

Recommended Maintenance

MilliCare® Textile and Carpet Care Service Network

Indoor Air Quality—CRI Green Label Plus™

GLP0793, Carpet Category 5Y

Recommended Installation Method(s)

Monolithic, Planks

WARRANTIES

Lifetime Face Fiber Wear
 Lifetime Antistatic
 Lifetime Floor Compatibility
 Lifetime Color Pattern Permanency
 Lifetime Floor Release

Lifetime Cushion Resiliency
 Lifetime Moisture Resistance
 Lifetime Delamination of Backing
 Lifetime Staining/Soiling (StainSmart®)
 Lifetime Dimensional Stability

Lifetime Tuft Bind
 Lifetime Edge Ravel
 Flammability



Declare.



This cushion-back carpet tile product is covered by one or more patents, published applications and/or patents pending. Specifications are subject to normal manufacturing tolerances and may be changed without prior notice. Copies of actual test results are available upon request.