Milliken

COMMON FACTOR

Acute

Modular Tile

Construction

Tufted, Textured Loop

Tile Size

1 m x 1 m (39.4" x 39.4")

Yarn Type

Milliken-Certified WearOn® Nylon

Stain Resist / Soil Release

StainSmart®

Dye Method

PrintWorks™ Precision Dyeing

Tufted Face Weight

 $20 \text{ oz/yd}^2 (678.1 \text{ g/m}^2)$

Gauge

1/10

Stitches Per Inch

10.3

Tufts

103/in² (1,595/100 cm²)

Finished Pile Height

0.14" (3.56 mm)

Finished Pile Thickness

0.11" (2.79 mm)

Average Density (Finished)

7.793

Standard Backing

PVC-Free WellBAC® Comfort Plus

Cushion

Available with TractionBack®

Recycled Content by Total Weight

Standard Backing: 35.9% Pre-Consumer, 0.0% Post-Consumer NSF 140 Platinum Backing Option: 27.3% Pre-Consumer, 10.0% Post-

Consumer

Embodied Carbon

17.32 (kg CO₂e)/m²

Nominal Total Thickness

0.35" (8.9 mm)

Nominal Total Weight

 $104.0 \text{ oz/yd}^2 (3,526 \text{ g/m}^2)$

Flammability (Radiant Panel

ASTM-E-648) ≥ 0.45 (Class I)

Smoke Density (NFPA-258-T or

ASTM-E-662)

< 450

Methenamine Pill Test (CPSC FF-1-70 or ASTM D 2859

Self-Extinguishing

Lightfastness (AATCC 16E)

≥ 4.0 at 80 Hours

Crocking (AATCC 165)

≥ 4.0 Wet or Dry

Static Electricity (AATCC-134) 20%

R.H.,70° F.

≤ 3.5 KV, Permanent Conductive Fiber

Texture Appearance Retention Rating (TARR)

Severe Traffic End-Use Applications

Recommended Maintenance

MilliCare® Textile and Carpet Care

Service Network

Indoor Air Quality—CRI Green Label

Plus™

GLP0793, Carpet Category 5Y

Recommended Installation Method(s)

Monolithic

WARRANTIES

Lifetime Face Fiber Wear Lifetime Antistatic Lifetime Floor Compatibility Lifetime Color Pattern Permanency Lifetime Floor Release

Lifetime Cushion Resiliency
Lifetime Moisture Resistance
Lifetime Delamination of Backing
Lifetime Staining/Soiling (StainSmart®)
Lifetime Dimensional Stability

Lifetime Tuft Bind Lifetime Edge Ravel Flammability













This cushion-back carpet tile product is covered by one or more patents, published applications and/ or patents pending. Specifications are subject to normal manufacturing tolerances and may be changed without prior notice. Copies of actual test results are available upon request.