Architectural Coatings

PPG UltraLast Interior Latex Paint + Primer Semi-Gloss

GENERAL DESCRIPTION

Backed by over 140 years of coatings expertise, *PPG UltraLast* Interior Paint + Primer* delivers breakthrough stain resistance and exceptional resistance to color loss and gloss change. Setting a new standard for super-premium interior paints, *PPG UltraLast* offers unprecedented washability - even in low-sheen finishes and deep colors. Proprietary *PPG* CLEAN-SURFACE TECHNOLOGY™ is a powerful integration of automotive and industrial coatings technology that keeps stains, grime and scuffs at the surface, where all-purpose cleaners can remove them easily. Interior walls will look clean and fresh until they are ready for a change of color.

*Separate primer or multiple coats may be required. See COVERAGE for details.

RECOMMENDED SUBSTRATES

Concrete/Masonry	Gypsum Wallboard-Drywall
Concrete Block (CMU)	Plaster
Ferrous Metal	Wood

CONFORMANCE STANDARDS

Compliant with all US VOC regulations as of 07/2024

PRODUCT INFORMATION

13-510	White & Pastel Base (Base 1)
13-520	Midtone Base (Base 2)*
13-540	Ultra Deep Base (Base 3)*

*Must be tinted before use. Refer to the appropriate color formula book, automatic tinting equipment, and or computer color matching system for color formulas and tinting instructions.

PACKAGING

Quart (946 mL)
1-Gallon (3.78 L)
5-Gallon (18.9 L)

PRODUCT DATA

PRODUCT TYPE:	Acrylic Latex
SHEEN:	Semi-Gloss, 45-65 @60º
VOLUME SOLIDS*:	39% +/- 2%
WEIGHT SOLIDS*:	53% +/- 2%
WEIGHT/GALLON*:	10.7 lbs. (4.9 kg) +/- 0.2 lbs. (91 g)
VOC:	< 50 g/L (0.4 lbs./gal.)

*Product data calculated on product 13-510.

COVERAGE: Up to 400 sq. ft. (37 sq. meters) per U.S. Gallon (3.78L) on smooth, nonporous surfaces.

Wet Film Thickness:	4 mils
Wet Microns:	102
Dry Film Thickness:	1.6 mils
Dry Microns:	41

Coverage figures do not include material loss due to surface irregularities and porosity, or material loss due to application method or mixing. Some surfaces including uncoated substrates, repaired surfaces, porous surfaces, stained areas, and drastic color changes may require a primer or more than one coat to achieve a uniform finish and complete hide.

DRYING TIME: Dry time @ 77ºF (25ºC); 50% relative humidity.

To Touch:	30-60 minutes
To Recoat:	2-4 hours
To Full Cure:	30 days

Drying times listed may vary depending on temperature, humidity, film build, color, and air movement. Wait at least 30 days after painting before cleaning the surface with a non-abrasive, mild cleanser. Very deep colors may require longer to fully cure.

CLEANUP: Clean tools with warm, soapy water.

DISPOSAL: Contact your local environmental regulatory agency for guidance on disposal of unused product. Do not pour down a drain or storm sewer.

FLASH POINT: Over 200ºF (93ºC)

FEATURES / BENEFITS

Features	Benefits
Engineered for unmatched washability	Longest lasting freshly painted look*, compare to conventions latex paints
Repels the most difficult stains	Stains wash easily away
Exceptional burnish and mar resistance	Highly resistant to gloss change and color loss from cleaning and abrasion
Low VOC, < 50 g/L	Low odor, compliant with all US VOC regulations
Specifically formulated to resist mildew on the paint film	Resists stains and deterioration caused by mildew

*Longest lasting freshly painted look is based on the combination of resistance to stains, gloss change, and marring.

Read Label and Safety Data Sheet prior to use. See other cautions on last page.

GENERAL SURFACE PREPARATION

Surface must be clean and dry. Remove all loose, peeling paint, dirt, grease, and any other surface contaminants. Putty all nail holes and caulk all cracks and open seams. Sand all glossy, rough, and patched surfaces. Plaster, concrete, and masonry surfaces must be completely dry, free of efflorescence, and allowed to cure for 30 days prior to painting. When applied to an uncoated substrate or to bare wood, two coats are required with the first coat acting as the primer. For severe stains, water marks, and other challenging conditions, such as bare metal or chalky surfaces, use an appropriate specialty primer.

WARNING! If you scrape, sand, or remove old paint, you may release lead dust or fumes. LEAD IS TOXIC. EXPOSURE TO LEAD DUST OR FUMES CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a properly fitted NIOSH-approved respirator and prevent skin contact to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the USEPA National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead. Follow these instructions to control exposure to other hazardous substances that may be released during surface preparation.

CONCRETE/MASONRY: New concrete and masonry should cure for at least 30 days and preferably 90 days prior to priming and painting. The pH of the substrate must be less than 10 before painting.

CONCRETE BLOCK (CMU): Mortar should cure for at least 30 days and preferably 90 days prior to painting. Fill block with an appropriate block filler.

FERROUS METAL: The surface must be cleaned thoroughly to remove any dust, rust, and surface contaminants, and then primed with a metal primer.

GYPSUM WALLBOARD-DRYWALL: Nails or screws should be countersunk, and they along with any indentations should be mudded flush with the surface, sanded smooth and cleaned to remove any dust prior to painting the substrate.

PLASTER: Plaster, hardcoat, skim coat, or other alkaline surfaces should be allowed to cure for at least 30 days prior to priming and painting. The pH of the substrate must be less than 10 before painting.

WOOD: Countersink all nails, putty flush with surface. Unpainted wood or wood in poor condition should be sanded smooth, wiped clean, then primed. Any knots or resinous areas must be sealed before painting.

RECOMMENDED PRIMERS

Concrete/Masonry	4-603XI, 17-921XI
Concrete Block (CMU)	6-7, 6-15XI
Ferrous Metal	90-1908, 90-1909, 90-1912
Gypsum Wallboard-Drywall	6-2, 6-4, 9-900, 12-900XI, 17-921XI, Self-priming
Plaster	4-603XI, 17-921XI, Self-priming
Wood	6-2, 9-900, 12-900XI, 17-921XI, sSlf-priming

LIMITATIONS OF USE

FOR INTERIOR USE ONLY. Apply when air, product and surface temperatures are between 50ºF (10ºC) and 90ºF (32ºC).

Not recommended for use on floors.

PROTECT FROM FREEZING.

APPLICATION INFORMATION

Stir thoroughly before using and occasionally when in use. When using more than one can of the same color, intermix to ensure color uniformity. USE WITH ADEQUATE VENTILATION. KEEP OUT OF REACH OF CHILDREN. Read all label and Safety Data Sheet (SDS) information prior to use. SDS are available through our web site or by calling 1-800-441-9695.

Application Equipment: Apply with a high-quality brush, roller, paint pad, or by spray equipment. Where necessary, apply a second coat and allow each coat to dry thoroughly before applying the next coat.

Airless Spray: Pressure 1500 to 2000 psi; tip 0.015" to 0.021". Spray equipment must be handled with due care and in accordance with manufacturer's recommendation. High-pressure injection of coatings into the skin by airless equipment may cause serious injury.

Brush: Polyester/Nylon Brush
Roller (nap roller cover): 3/8" - 3/4"
Thinning: Do not thin.

Permissible temperatures during application:

Material:	50 to 90ºF	10 to 32ºC
Ambient:	50 to 90ºF	10 to 32ºC
Substrate:	50 to 90ºF	10 to 32ºC

PRECAUTIONS

WARNING! HARMFUL IF INHALED. HARMFUL IF SWALLOWED. Do not breathe vapor or mist. Do not swallow. Keep container tightly closed and sealed until ready for use. Wash thoroughly after handling. Provide fresh air ventilation during and after application and drying. Avoid the inhalation of dust, particulates, spray or mist arising from the application of this preparation. Use personal protective equipment as required. **Note: These warnings encompass the product series. Prior to use, read and follow product specific SDS and label information. FIRST AID:** If swallowed, rinse mouth with water (only if the person is conscious). Call physician immediately. Do not induce vomiting unless directed to do so by medical personnel. If in eyes, rinse with water for 15 minutes. Check for and remove any contact lenses. If on skin, rinse well with water. Wash with soap and water. Get medical attention if irritation develops. If inhaled, remove to fresh air. Call physician immediately. Contains isothiazolinones. May cause allergic reaction. Keep out of the reach of children. For workplace use, an SDS is available from your retailer or by calling (412) 492-5555. EMERGENCY SPILL INFORMATION: (412) 434-4515 (U.S.).

© 2024 PPG Industries, Inc. All Rights Reserved. The *PPG logo* is a registered trademark of PPG Industries Ohio, Inc. *PPG UltraLast* is a registered trademark of PPG Architectural Finishes, Inc. *Clean-Surface Technology* is a trademark of PPG Architectural Finishes, Inc.

PPG Architectural Finishes, Inc. believes the technical data presented is currently accurate: however, no guarantee of accuracy, comprehensiveness, or performance is given or implied. Improvements in coatings technology may cause future technical data to vary from what is in this bulletin. For complete, up-to-date technical information, call 1-800-441-9695.