



Architectural Coatings

PPG Barn & Fence Exterior Latex Flat

GENERAL DESCRIPTION

PPG Barn and Fence Latex Paints are good quality, economical paints recommended for general use on exterior wood surfaces. This product has good hiding power and offers the convenience of soap and water clean up. Available in a ready mix black, red, and white, these paints are designed for new or previously painted barns, sheds, silos, outbuildings, fences and garages.

RECOMMENDED SUBSTRATES

Aluminum	Metal
Fiber Cement Board	Wood
Masonry	

CONFORMANCE STANDARDS

VOC compliant in all regulated areas

PRODUCT INFORMATION

37-183	Black
37-710	Red
37-762	White

PACKAGING

5-Gallon (18.9 L)

PRODUCT DATA

PRODUCT TYPE:	Latex
SHEEN:	Flat
VOLUME SOLIDS*:	25% +/- 2%
WEIGHT SOLIDS*:	43% +/- 2%
WEIGHT/GALLON*:	10.9 lbs. (4.9 kg) +/- 0.2 lbs. (91 g)
VOC:	<50 g/L (0.4 lbs./gal.)

*Product data calculated on product 37-762.

COVERAGE: Approximately 400 sq. ft. (28 to 37 sq. meters) per U.S. Gallon (3.78L) on smooth, nonporous surfaces.

Wet Film Thickness:	4.0 mils
Wet Microns:	102
Dry Film Thickness:	1.0 mils
Dry Microns:	25

Coverage figures do not include loss due to surface irregularities and porosity or material loss due to application method or mixing.

DRYING TIME: Dry time @ 77°F (25°C); 50% relative humidity.

To Touch:	30 minutes
To Recoat:	1 hour
To Full Cure:	30 days

Drying times listed may vary depending on temperature, humidity, film build, color, and air movement.

CLEANUP: Clean tools with warm, soapy water.

DISPOSAL: Contact your local environmental regulatory agency for guidance on disposal of unused product. Do not pour down a drain or storm sewer.

FLASH POINT: Over 200°F (93°C)

FEATURES / BENEFITS**Features**

- Highly economical
- Good hiding power and coverage
- Uniform flat finish
- Protects wood
- Fast dry time
- Easy to apply
- Easy soap and water clean-up
- VOC Compliant

Benefits

- Good quality at a reasonable price
- Provides uniform finish
- Consistent finished appearance
- Keeps wood looking new longer
- Turns jobs quicker
- Brush, roller, or spray application
- Safe waterborne formula
- Lower than Federal AIM, OTC, and LADCO regulations

Read Label and Safety Data Sheet prior to use. See other cautions on last page.

GENERAL SURFACE PREPARATION

Surface must be clean and dry. Remove all loose, peeling paint, dirt, mildew, grease, oil, chalk, rust, and any other surface contaminants. Repair all moisture problems. Blistering and peeling issues are commonly caused by moisture behind the paint film. Putty all nail holes and caulk all cracks and open seams. Sand all glossy, rough and patched surfaces. For new masonry and concrete, allow to dry and cure thoroughly (30 days), then prime with an alkali-resistant primer. When applied to bare wood, two coats are required with the first coat acting as the primer. For metal, tannin staining woods, or chalky surfaces, use of the appropriate high quality specialty primer is recommended for best results.

WARNING! If you scrape, sand, or remove old paint, you may release lead dust or fumes. LEAD IS TOXIC. EXPOSURE TO LEAD DUST OR FUMES CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a properly fitted NIOSH-approved respirator and prevent skin contact to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the USEPA National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead. Follow these instructions to control exposure to other hazardous substances that may be released during surface preparation.

ALUMINUM: This substrate may present potential adhesion problems. Any coating applied directly to aluminum should be spot applied, allowed to cure overnight, and then evaluated for adhesion. If adhesion is good, the application may proceed.

BRICK: New brick and mortar should cure for at least 30 days and preferably 90 days prior to priming and painting. The pH of the substrate must be less than 10 before priming. Painting glazed brick is not recommended due to potential adhesion problems.

CONCRETE and MASONRY: New masonry should cure for at least 30 days and preferably 90 days prior to priming and painting. The pH of the substrate must be less than 10 before priming with an alkali resistant primer.

FERROUS METAL: The surface must be cleaned thoroughly to remove any dust, rust, and surface contaminants, and then primed.

FIBER CEMENT: Fiber cement siding and trim board may present potential adhesion, alkali burn, and efflorescence problems. New board should be aged for at least 30 days prior to priming and painting. The pH of the substrate must be less than 10 and the moisture content must be less than 12% prior to priming and topcoating. All cracks and opens seams should be caulked to prevent water penetration. Pre-primed board from the manufacturer may not be uniformly or completely sealed. It is recommended that an alkali resistant primer be applied to ensure complete and uniform sealing prior to topcoating.

WOOD: Unpainted wood or wood in poor condition should be sanded smooth, wiped clean, then primed. Any knots or resinous areas must be primed before painting. Countersink all nails, putty flush with surface, then prime.

RECOMMENDED PRIMERS

Aluminum	17-921XI
Brick	4-503, 4-603XI, 17-921XI
Concrete & Masonry	4-503, 4-603XI, 17-921XI
Ferrous Metal	4020, 90-712, 90-912
Fiber Cement	4-2, 4-503, 4-603XI
Wood	17-921XI, Self-priming

LIMITATIONS OF USE

Apply only when air, surface, and product temperatures are between 50°F (10°C) and 90°F (32°C) and at least 5°F (3°C) above the dew point. Air and surface temperatures must remain between 50°F (10°C) and 90°F (32°C) for the next 48 hours. Avoid painting in direct sunlight or on hot surfaces. Do not apply late in the day when dew and condensation are likely to form or if rain or snow is expected. Where necessary, apply a second coat and allow each coat to dry thoroughly before applying the next coat.

PROTECT FROM FREEZING.

Not recommended for use on steps or floors.

While this product provides a mildew resistant coating, growth may still occur if the substrate is not properly prepared prior to painting and/or if the substrate is consistently exposed to conditions conducive to mold, mildew, and algae.

APPLICATION INFORMATION

Stir thoroughly before using and occasionally when in use. When using more than one can of the same color, intermix to ensure color uniformity. USE WITH ADEQUATE VENTILATION. KEEP OUT OF REACH OF CHILDREN. Read all label and Safety Data Sheet (SDS) information prior to use. SDS are available through our web site or by calling 1-800-441-9695.

Application Equipment: Apply with a high-quality brush, roller, paint pad, or by spray equipment.

Airless Spray: Pressure 1800 to 2400 psi; tip 0.015" to 0.019". Spray equipment must be handled with due care and in accordance with manufacturer's recommendation. High-pressure injection of coatings into the skin by airless equipment may cause serious injury.

Brush: Polyester/Nylon Brush

Roller (nap roller cover): 3/8" - 3/4"

Thinning: Do not thin.

Permissible temperatures during application:

Material:	50 to 90°F	10 to 32°C
Ambient:	50 to 90°F	10 to 32°C
Substrate:	50 to 90°F	10 to 32°C

PRECAUTIONS

WARNING! HARMFUL IF INHALED. HARMFUL IF SWALLOWED. Sanding and grinding dusts may be harmful if inhaled. Do not breathe vapor or mist. Do not swallow. Keep container tightly closed and sealed until ready for use. Wash thoroughly after handling. Provide fresh air ventilation during and after application and drying. Avoid the inhalation of dust, particulates, spray or mist arising from the application of this preparation. Use personal protective equipment as required. DANGER - RAGS, STEEL WOOL OR WASTE SOAKED WITH BARN & FENCE PAINT MAY SPONTANEOUSLY CATCH FIRE IF IMPROPERLY DISCARDED. IMMEDIATELY AFTER EACH USE, PLACE RAGS, STEEL WOOL OR WASTE IN A SEALED WATER-FILLED METAL CONTAINER. **Note: These warnings encompass the product series. Prior to use, read and follow product-specific SDS and label information.** **FIRST AID:** If swallowed, rinse mouth with water (only if the person is conscious). Call physician immediately. Do not induce vomiting unless directed to do so by medical personnel. If in eyes, rinse with water for 15 minutes. Check for and remove any contact lenses. If on skin, rinse well with water. Wash with soap and water. Get medical attention if irritation develops. If inhaled, remove to fresh air. Call physician immediately. For workplace use, an SDS is available from your retailer or by calling (412) 492-5555. EMERGENCY SPILL INFORMATION: (412) 434-4515 (U.S.).

© 2019 PPG Industries, Inc. All Rights Reserved. The PPG Logo is a registered trademark of PPG Industries Ohio, Inc.

PPG Architectural Finishes, Inc. believes the technical data presented is currently accurate: however, no guarantee of accuracy, comprehensiveness, or performance is given or implied. Improvements in coatings technology may cause future technical data to vary from what is in this bulletin. For complete, up-to-date technical information, call 1-800-441-9695.



PPG Architectural Finishes, Inc.
One PPG Place
Pittsburgh, PA 15272
www.ppgpaints.com

Technical Services
1-800-441-9695

Architect/Specifier
1-888-PPG-IDEA

PPG Architectural Coatings Canada Inc.
1550 rue Ampère, Suite 500
Boucherville (Quebec) J4B 7L4

37-762 2/2020