

**CF07 Clear PET Glass Film was tested and met the following flammability requirements:**

ASTM E 84 Adhered Class A



GOVMARK

96-D Allen Boulevard  
Farmingdale, New York 11735-5626 USA  
Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956  
email: govmark.accounting@sgs.com

Page 1

Received: 10/17/2019	Completed: 10/23/2019	Letter: J	JG	P.O.#:	Test Report #:	3-35083-0-
----------------------	-----------------------	-----------	----	--------	----------------	------------

Client's Identification	Product Identification: GF07 Glass Film Printed.
-------------------------	--------------------------------------------------

Tested For: <b>Adity Phadnis</b> Designtex 357 County Avenue Secaucus, NJ 07094	Key Test: ASTM E84/ACT  Tel: 1-(201)-917-7743 Fax: 1-(201)-917-7764	765  Ext:
------------------------------------------------------------------------------------------	------------------------------------------------------------------------------	-----------------

Test Category: Tunnel Test    Specifier: ACT    LE 2018; V 01/19    PC: ME    dl/SM BB/mg

TEST PERFORMED: ASTM E84 - Standard Test Method for Surface Burning Characteristics of Building Materials [LE 2018a; V 9/18] --

As cited by the Association of Contract Textiles (ACT) Voluntary Performance Guidelines (August 2018)

APPROXIMATE THICKNESS OF SPECIMEN (as measured by SGS Govmark): 0.005"

SPECIMEN WEIGHT (to include substrate when applicable):

Prior to Conditioning: 92.7 lbs.

Stabilized Weight (taken twice within 24 hours): 92.5 lbs.

PRODUCT CATEGORY:

☐ Textile Type Product

☐ Vinyl Type Product

☒ Other than Textile Type or Vinyl Type Product: See "Client's Identification" section above

**BRIEF DESCRIPTION OF TEST:** This test method is used to determine the relative burning behavior of a material under defined test conditions. The test is performed in a 25 ft. long tunnel/duct-like apparatus and is often referred to as the "tunnel test". The test contemplates a calibration where Red Oak burns to the 24 ft. mark in 5.5 minutes  $\pm$  15 seconds. During the actual test, a 24 ft. long x 23" wide specimen rests horizontally in a ceiling configuration inside the test chamber facing downward and toward two upward oriented burners. A furnace lid that rests in a water trough seals the chamber tight. A cement board placed on the backside of each specimen assembly protects the furnace lid during the test. The near face of the specimen is subjected to a 4.5 ft. flame insult of approximately 88 kW for ten minutes. The time and distance of the spread of flame along the length of the specimen and the smoke developed as read by the photometric system are all recorded. The Flame Spread and Smoke Developed are reported as an Index.

-- See Page 3 for "Results" --

(Page 1 of 4)

File Copy



GOVMARK

96-D Allen Boulevard  
Farmingdale, New York 11735-5626 USA  
Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956  
email: govmark.accounting@sgs.com

Page 2

Received: 10/17/2019	Completed: 10/23/2019	Letter: J	JG	P.O.#:	Test Report #:	3-35083-0-
Client's Identification	Product Identification: GF07 Glass Film Printed.					
Tested For: Adity Phadnis Designtex 357 County Avenue Secaucus, NJ 07094			Key Test: ASTM E84/ACT  Tel: 1-(201)-917-7743 Fax: 1-(201)-917-7764			765  Ext:

## SPECIMEN MOUNTING:

- ☐ Self-supporting: The test specimen was rigid enough to be self-supporting when placed into test position. No additional support was required.
- ☒ Adhered to IRC: The test specimen was bonded to 1/4" Inorganic Reinforced Cement (IRC) boards.
- ☐ Adhered to Gypsum: The test specimen was adhered to 5/8" thick Type X gypsum board.
- ☐ Unadhered: The specimen was not adhered to any substrate. Instead, it was laid over a 2" hexagonal wire mesh screen and 1/4" rods.
- ☐ Other: \_\_\_\_\_

## SPECIMEN LENGTH: The 24 ft. length was comprised of:

- ☐ Continuous unbroken 24 ft. length
- ☒ Sections: ☒ Three 8 ft. sections butted end to end  
☐ Three 8 ft. sections positively joined  
☐ Other: \_\_\_\_\_

ADHESIVE (applied by SGS Govmark): ☐ No  
☒ Yes (specify): Roman Pro-880

OBSERVATIONS: ☒ No unusual observations  
☐ Delamination  
☐ Sagging  
☐ Shrinkage  
☐ Fallout (specimen displacement from ceiling mount)  
☐ Other: \_\_\_\_\_

REMARKS: ☒ None  
☐ Other: \_\_\_\_\_

(Page 2 of 4)

File Copy



GOVMARK

96-D Allen Boulevard  
Farmingdale, New York 11735-5626 USA  
Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956  
email: govmark.accounting@sgs.com

Page 3

Received: 10/17/2019 Completed: 10/23/2019 Letter: J JG P.O.#: Test Report #: 3-35083-0-

**Client's  
Identification**

Product Identification: GF07 Glass Film Printed.

**Tested For: Adity Phadnis**

Designtex  
357 County Avenue  
Secaucus, NJ 07094

Key Test: ASTM E84/ACT

765

Tel: 1-(201)-917-7743

Ext:

Fax: 1-(201)-917-7764

RESULTS: Flame Spread Index: 5  
Smoke Developed: 5

ROUNDING: Flame Spread Index value has been rounded to the nearest multiple of 5.  
Smoke Developed value has been rounded to:

Raw Data	Rounded
Less than 200	Nearest multiple of 5
200 or more	Nearest multiple of 50

## ACCEPTANCE CRITERIA (as cited by ACT):

	Flame Spread Index	Smoke Developed
Class A	0 -25	450 or less

NOTE: Class A is also known as Class 1 and may be so specified in some Codes.

CONCLUSION: Based on the reported Results and cited Acceptance Criteria, the item tested:

[x] Complies; [ ] Does not comply

DATA SUMMARY: Time to Ignition (minutes:seconds): 00:15  
Maximum Flame Spread "Distance" (feet): 0.9  
Maximum Flame Spread "Time" (seconds): 115

CODE CLASSIFICATION: Based on the reported Results and cited Code Classification System, the item tested is assigned a:

- ☒ Class I or A rating
- ☐ Class II or B rating
- ☐ Class III or C rating
- ☐ Fails to achieve a minimum classification thereby rendering the product unsuitable in terms of code requirement
- ☐ Based on product performance\*, ASTM E84 is not a suitable test method for the material.

\* Severe melt, drip, delamination or other behavior that destroys the continuity of the flame front such that a valid flame spread is unobtainable (See "Remarks" on Page 2 of 4.)

-- See Page 4 for "Code Classification System" --

(Page 3 of 4)

File Copy





GOVMARK

96-D Allen Boulevard  
Farmingdale, New York 11735-5626 USA  
Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956  
email: govmark.accounting@sgs.com

Page 4

Received: 10/17/2019 Completed: 10/23/2019 Letter: J JG P.O.#: Test Report #: 3-35083-0-

Client's Identification

Product Identification: GF07 Glass Film Printed.

Tested For: Adity Phadnis

Designtex  
357 County Avenue  
Secaucus, NJ 07094

Key Test: ASTM E84/ACT

765

Tel: 1-(201)-917-7743

Ext:

Fax: 1-(201)-917-7764

CODE CLASSIFICATION SYSTEM:

	Flame Spread Index	Smoke Developed
	-----	-----
Class I or A:	0 - 25	450 or less
Class II or B:	26 - 75	450 or less
Class III or C:	76 - 200	450 or less

LIMITATIONS OF THE ASTM E84 CLASSIFICATION SCHEME: Most building codes will accept the ASTM E84 classifications when the interior finish product is used in a sprinklered area. Certain local authorities such as NYC have more stringent requirements, i.e. Smoke Developed ranges from a maximum 25 to 100.

If the interior finish product is a textile or vinyl wall covering used in a non-sprinklered area, the NFPA 265 room corner fire test applies.

Certain products which give off excessive heat such as but not limited to cellular plastics, cellular foam (either with or without coverings as applicable), polypropylene, and high density polyethylene should be tested by NFPA 286 - Standard Methods of Fire Tests for Evaluating Contribution of Wall and Ceiling Interior Finish to Room Fire Growth. In Govmark's opinion, the codes require NFPA 286 for such products, even in sprinklered areas.

CERTIFICATION: I certify that the reported results were obtained after testing specimens in accordance with the procedures and equipment specified above.

Phyllis Pettit

Test Engineer: Jillian Guillem

AUTHORIZED SIGNATURE

SGS GOVMARK

/mg

/pm


OCT 28 2019

Enclosure: Graphs

(Page 4 of 4)

Test Method : ASTM E84  
 Test Report # : 3-35083-0-J  
 Date : 10/23/2019  
 Client : Designtex  
 Operator : Jillian Brown  
 Details of Preparation : The test specimen was adhered to 1/4" Inorganic Reinforced Cement (IRC) boards using Roman Pro 880 adhesive. The 24 ft specimen was comprised of three 8 ft sections butted end to end.  
 Observations : No unusual observations

Area Under Flame Curve (ft min) : 7.39  
 Raw Flame Spread Index (ft min) : 3.81  
 Rounded Flame Spread Index (ft min) : 5  
 Ignition Time : 00:15 mm:ss  
 Area Under Smoke Curve (%A min) : 4.72  
 Raw Smoke-Developed Index : 4.68  
 Rounded Smoke-Developed Index : 5  
 Total Gas Flow(L) : 1425.2  
 Total Gas Flow(ft<sup>3</sup>) : 50.3  
 Maximum Flame Front Achieved(ft) : 0.9 (@115s)



Test Method : ASTM E84  
Test Report # : 3-35083-0-J

