

3538 Pika was tested and met the following flammability requirements:

CA TB 117-2013

ISO/IEC 17025 Third Party Test Report

DATE: May 12, 2023

FILE: DESTEX.A050523D-R1

CLIENT: Designtex
357 County Ave.
Secaucus, NJ 07094

ATTN: Teesha Prezeau

SAMPLE IDENTIFIED BY CLIENT AS:

Fabric Submitted
Name: Pika
Style #: 3538 101, 12 oz/Lyd
Lot #: 864490 93709
Backing: Stain Resistant
53% Acrylic, 47% Polyester
Color Flax (Beige)

TEST PROCEDURES:

TEST RESULTS:

CALIFORNIA TECHNICAL BULLETIN 117-2013 SECTION 1 COVER FABRIC TEST

	CHAR LENGTH *****	OPEN FLAME *****	SMOLDER TIME OVER 45 MINUTES *****
SPECIMEN 1:	17 mm	No	No
SPECIMEN 2:	15 mm	No	No
SPECIMEN 3:	15 mm	No	No

TEST RESULT: PASS

A material is considered to pass or fail based on the following criteria:

1. A single mock-up test specimen fails to meet the requirements of this test procedure if any of the following criteria occurs:
 - a) The mock-up test specimen continues to smolder after the 45-minute test duration.
 - b) A char develops more than 1.8 inches (45 mm) in any direction from the cigarette on the cover fabric measured from its nearest point.
 - c) The mock-up test specimen transitions to open flaming.
2. The cover fabric passes the test if three initial mock-up specimens pass the test, i.e., the cigarettes burn their full length and the mock-up are no longer smoldering.
3. If more than one initial specimens fails, the cover fabric fails the test.
4. If any one of the three initial specimen fails, repeat the test on an additional three specimens.
5. If all three additional specimens pass the test, the cover fabric passes the test. If any one of the three additional specimens fails, the cover fabric fails the test.

This report has been revised to amend sample identification. This report replaces report # DESTEX.A050523D dated May 11, 2023.

Signed For The Company By

Joseph Lin
Laboratory Manager

CF/05



Stacy Sadowy
Quality Assurance Manager

