

**3403 Sorano was tested and met the following flammability requirements:**

CA TB 117-2013

## ISO/IEC 17025 Third Party Test Report

**DATE:** March 9, 2023  
**CLIENT:** Design Tex Inc.  
200 Varick Street, 8th Floor  
New York, NY 10014

**FILE:** DESTEX.A030323F

**ATTN:** Teesha Prezeau

**SAMPLE IDENTIFIED BY CLIENT AS:**

Fabric Submitted  
Name: Sorano  
Style #: 3403, 54", Weight: 28 oz/Lyd  
Finish: Advanced Protective Top Coat, Backing: Polyester Knit  
100% Vinyl  
Color Smokey (Grey)

**TEST PROCEDURE:**

**TEST RESULTS:**

**CALIFORNIA  
TECHNICAL BULLETIN 117-2013**

\*\*\*\*\*

	CHAR LENGTH *****	OPEN FLAME *****	SMOULDER TIME OVER 45 MINUTES *****
SPECIMEN 1:	SE	N	N
SPECIMEN 2:	SE	N	N
SPECIMEN 3:	SE	N	N

**SE: SELF-EXTINGUISHED**

**TEST RESULT: PASS**

A material is considered to pass or fail based on the following criteria:

1. A single mock-up test specimen fails to meet the requirements of this test procedure if any of the following criteria occurs:
  - a) The mock-up test specimen continues to smolder after the 45-minute test duration.
  - b) A char develops more than 1.8 inches (45 mm) in any direction from the cigarette on the cover fabric measured from its nearest point.
  - c) The mock-up test specimen transitions to open flaming.
2. The cover fabric passes the test if three initial mock-up specimens pass the test, i.e., the cigarettes burn their full length and the mock-up are no longer smoldering.
3. If more than one initial specimens fails, the cover fabric fails the test.
4. If any one of the three initial specimen fails, repeat the test on an additional three specimens.
5. If all three additional specimens pass the test, the cover fabric passes the test. If any one of the three additional specimens fails, the cover fabric fails the test.

Signed For The Company By

  
Joseph Lin  
Laboratory Manager



  
Stacy Sadowy  
Quality Assurance Manager

CF/03

