

CT16 Voile was tested and met the following flammability requirements:

NFPA 701 TM#1



96-D Allen Boulevard
Farmingdale, New York 11735-5626 USA
Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956
e-mail: testing@govmark.com

Page 1

Received: 04/19/2018 Completed: 04/20/2018 Letter: A BG P.O.#: Test Report #: 3-25627-0-

Client's Identification Style: DT 16 Voile, printed. Composition: 100% Polyester. Weight: 4.4 oz/yd. Additional Information: 122" width.

Tested For: Adity Phadnis Key Test: NFPA 701-2015 TM#1 250
Designtex
357 County Avenue
Secaucus, NJ 07094
Tel: 1-(201)-917-7743 Ext:
Fax: 1-(201)-917-7764

LE: 2015 NE: 2019 V: 11/17 NTR 04/16 PC: 0.5H DL/jd

TEST PERFORMED: NFPA 701 - Standard Methods of Fire Tests for Flame Propagation of Textiles and Films - 2015 Edition - Test Method #1

PRODUCT CONFIGURATION: ☒ Single Layer; ☐ Multi Layer

RESULTS REPORTED: ☒ Initially; ☐ After 3 dry cleanings; ☐ After 5 launderings @ 160°F

RESULTS:

| Specimen # | Afterflame* (seconds) | Flaming Drip (seconds) | Weight Loss (percent) |
|------------|--------------------------|---------------------------|--------------------------|
| 1 | 0 | 0.0 | 28.6 |
| 2 | 0 | 1.4 | 42.9 |
| 3 | 0 | 0.0 | 23.1 |
| 4 | 0 | 2.0 | 23.1 |
| 5 | 0 | 0.0 | 30.8 |
| 6 | 0 | 1.7 | 38.5 |
| 7 | 0 | 1.4 | 23.1 |
| 8 | 0 | 2.5 | 28.6 |
| 9 | 0 | 0.0 | 30.8 |
| 10 | 0 | 1.4 | 23.1 |
| Mean: | 1.0 | Mean: | 29.2 |

STATISTICAL VALUES: SD = 6.9 3 SD = 20.7 Mean + 3 SD = 49.9

ABBREVIATIONS USED: SD = Standard deviation. NT = Not tested.

APPROXIMATE WEIGHT OF MATERIAL (as measured by Govmark): 44 g/m²

PRECONDITIONING: ☒ 0.5 hr @ 220°F (Standard)
☐ 24 hrs @ 68±9°F (Alternate: Material shrinks/distorts @ 220°F)

CONVERSION FACTOR: g/m² ÷ 28.35 x .835 = oz/yd²

NOTE:

1. All specimens prepared in the length direction.
2. See addendum for individual specimen weights.

(Page 1 of 3)

File Copy



96-D Allen Boulevard
Farmingdale, New York 11735-5626 USA
Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956
e-mail: testing@govmark.com

Page 2

| | | | | | | |
|--|--|-----------|--|--------|----------------|------------|
| Received: 04/19/2018 | Completed: 04/20/2018 | Letter: A | BG | P.O.#: | Test Report #: | 3-25627-0- |
| Client's Identification | Style: DT 16 Voile, printed. Composition: 100% Polyester. Weight: 4.4 oz/yard. Additional Information: 122" width. | | | | | |
| Tested For: Adity Phadnis | | | Key Test: NFPA 701-2015 TM#1 | | | 250 |
| Designtex 357 County Avenue Secaucus, NJ 07094 | | | Tel: 1-(201)-917-7743 Fax: 1-(201)-917-7764 | | | Ext: |

REMARKS:

- ☒ Flames did not project above the top of the specimen.
☐ Flames projected above the top of the specimen; Specimen #'s _____
☐ Other: _____

FAILURE CRITERIA: As cited by NFPA 701 - 2015 Edition Test Method #1

| Afterflame | Flaming Drip (Mean) | Weight Loss (percent) | |
|------------|------------------------|-----------------------|-----------------------|
| | | Mean | Individual Specimen |
| * | Exceeds 2 seconds | Exceeds 40% | Exceeds Mean + 3 SD** |


CONCLUSION: Based on the Results on page 1 and the above Failure Criteria cited by NFPA 701 - 2015 Edition Test Method #1, the item tested:

- ☒ Passes; ☐ Fails; ☐ Requires testing of 10 additional specimens
i.e. only one individual specimen failure was noted

* Afterflame is required to be recorded; however, the NFPA document does not factor it into the Failure Criteria reporting requirements. It should be noted that excessive afterflames could be cause for rejection by local fire authorities performing "match" field tests.

** See "Discussion" on Page 3.

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified above.



AUTHORIZED SIGNATURE
GOVMARK
/ac
/pm

Phyllis A. Pettit
APR 25 2018



96-D Allen Boulevard
Farmingdale, New York 11735-5626 USA
Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956
e-mail: testing@govmark.com

Page 3

| | | | | | | |
|--|--|-----------|--|--------|----------------|------------|
| Received:04/19/2018 | Completed:04/20/2018 | Letter: A | BG | P.O.#: | Test Report #: | 3-25627-0- |
| Client's Identification | Style: DT 16 Voile, printed. Composition: 100% Polyester. Weight: 4.4 oz/yard. Additional Information: 122" width. | | | | | |
| Tested For: Adity Phadnis | | | Key Test: NFPA 701-2015 TM#1 | | | 250 |
| DesignTex 357 County Avenue Secaucus, NJ 07094 | | | Tel: 1-(201)-917-7743 Fax: 1-(201)-917-7764 | | | Ext: |

**** DISCUSSION:**

Weight Loss - Individual Specimen Failure:

The NFPA 701 document, as written, provides for a statistical calculation which provides for retest and a potential failure if any individual value exceeds the mean by three standard deviations. Govmark is of the opinion that this cannot mathematically occur, i.e. no individual result is mathematically capable of exceeding the mean plus three standard deviations. Therefore, in effect, Govmark is of the opinion that this "individual specimen criteria" has no meaning, since it cannot possibly result in a nonconformance.

Client Name : Designtex
Addendum to Test Report # : 3-25627-0
Test : NFPA 701

| Specimen # | Weight Before Test (g) | Weight After Test (g) | Percent Weight Loss |
|------------|--------------------------|-------------------------|---------------------|
| 1 | 2.80 | 2.00 | 28.6 |
| 2 | 2.80 | 1.60 | 42.9 |
| 3 | 2.60 | 2.00 | 23.1 |
| 4 | 2.60 | 2.00 | 23.1 |
| 5 | 2.60 | 1.80 | 30.8 |
| 6 | 2.60 | 1.60 | 38.5 |
| 7 | 2.60 | 2.00 | 23.1 |
| 8 | 2.80 | 2.00 | 28.6 |
| 9 | 2.60 | 1.80 | 30.8 |
| 10 | 2.60 | 2.00 | 23.1 |

Mean Percent Weight Loss : 29.2
Standard Deviation : 6.9
3 x Standard Deviation : 20.7
Mean + 3 x Standard Deviation : 49.9

APR 25 2018

