CT102 Interface



## Installation Method





Ashlar

Quarter turn

All product specifications reflect averages derived from product sample testing, are subject to normal manufacturing and testing tolerances and inherent pattern variances, and may be changed without notice. For more information about these and other important attributes of the product(s) described herein, including recycled content and product warranty information, please see www.interface.com/disclaimer.

| Product CT102 Color                    | Steel <b>Collection</b> Common Theme Collection <b>Backing</b> GlasBac™                                   |
|--|---|
| <b>Product Specifications</b>          |   |
| Product Number                         | 1425702500  |
| Product Construction                   | Tufted Sheared  |
| Yarn System                            | Post-Consumer Content Nylon   |
| Yarn Manufacturer                      | Universal   |
| Dye Method                             | 100% Solution Dyed  |
| Soil/Stain Protection                  | Protekt <sup>2</sup> ®  |
| Preservative Protection                | Intersept®  |
| More Product Specifica                 | ations  |
|  | Imperial Metric   |
| Tufted Yarn Weight                     | 22 oz/yd² 746 g/m²  |
| Machine Gauge                          | 1/10 in 39.4 ends/10cm  |
| Pile Height                            | 0.18 in 4.60 mm   |
| Pile Thickness                         | 0.13 in 3.50 mm   |
| Stitches                               | 12.30 /in 48.42 ends/10cm   |
| Pile Density                           | 6,092 oz/yd³ 225,890 g/m³   |
| Size                                   | 19.69 in x 19.69 in 50cm x 50cm   |
| Performance Specificat                 | ions  |
| Flooring Radiant Panel                 | (ASTM E-648) Passes   |
| Smoke Density                          | (ASTM E-662) ≤ 450  |
| Flammability                           | Passes Methenamine Pill Test (DOC-FF1-70)   |
| Lightfastness                          | (AATCC 16 - E) ≥ 4.0 @ 60 AFU's   |
| Static                                 | (AATCC - 134) < 3.0 KV  |
| Dimensional Stability                  | AACHEN Din 54318 < 0.10%  |
| Traffic Classification                 | Moderate  |
| Fiber Modification Ratio               |   |
| Preservative Efficacy                  | (AATCC 174 Parts 2&3) 99% Reduction/No Mold 7 Days (ASTM E-2471) Complete Inhibition                      |
| Health + Environmenta                  | al Specifications   |
| Embodied Carbon<br>(Cradle to Gate)    | 4.93 Kg CO <sub>2</sub> /M <sup>2</sup>   |
| Total Recycled Content                 | 64.38 %   |
| Recycled Content<br>(Pre Consumer)     | 63.21 %   |
| Recycled Content<br>(Post Consumer)    | 1.17 %  |
| Indoor Air Quality                     | Green Label Plus #GLP0820   |
| Material Composition                   | Free of Added Heavy Metals, Formaldehyde, Fluorinated Chemicals (PFAS), and Halogenated Flame Retardants. |
| Disclosure of<br>Environmental Impacts | Environmental Product Declaration   |
| Disclosure of Product<br>Ingredients   | Health Product Declaration  |
| Environmental<br>Certifications        | NSF/ANSI 140 Gold   |
| LEED v4                                | Contributes to multiple IEQ and MR credits  |
| End of Life                            | Carpet to Carpet Recycling through ReEntry®   |
| Technical Information                  |   |
| Installation                           | Interface Installation Guidelines   |
| Maintenance                            | Recommended Interface Maintenance Guidelines  |
| Reclamation                            | Recyclable through ReEntry® - Call 1.888.733.6873 (U.S.) /<br>1.866.398.3191 (Canada)                     |
| Warranty                               | 15 Year Standard Carpet Warranty  |
| Installation Method                    | Quarter Turn<br>Ashlar  |
| Manufacturing Location                 | ISO 9001 & 14001 Certified facilities in Troup County, Georgia, United States                             |