



Electric Edit #11611

Product Specification

Face Construction	Imperial		Metric		
Construction	Stratatec® Patterned Loop				
Gauge	5/64		50.4	rows/10 cm	
Stitches per Inch	10.0		39.4	pu/10 cm	
Tuft Density	128	tufts/sq in	19.8	tufts/sq cm	
Pile Height Average	0.141	inch	3.6	mm	
Pile Thickness	0.070	inch	1.8	mm	
Total Finished Thickness	ethos® Modular with Omnicoat Technology®: 0.203 inch Flex-Aire Modular® Cushion: 0.309 inch				
Pile Density	6,686	oz/cu yd	247.4	kg/cu m	Kilotex 7.9
Fiber System	Dynex SD® Nylon (Permanent Stain Resistance)				
Dye Method	Solution Dyed				
Fluorine-Free Soil Protection	Eco-Ensure: C2C Certified® Material Health - Platinum (v3.1)				
Primary Tufting Substrate	Synthetic Non-Woven				
Pattern Match	Not Required				

Third Party Environmental Certifications

Product	Green Label Plus Certified	NSF 140 SCS Certified	Cradle to Cradle Certified™ v3.1
ethos® Modular with Omnicoat Technology®	GLP8320	Gold	Silver
Flex-Aire Modular® Cushion	GLP6558	Gold	

Recycled Content	Overall	Post-Consumer	Pre-Consumer
ethos® Modular with Omnicoat Technology®	56 - 79%	30 - 43%	26 - 36%
Flex-Aire Modular® Cushion	28 - 46%	22 - 34%	3 - 13%

Product Testing/Information

Antimicrobial Chemicals	No antimicrobials (EPA Registered pesticides) added to product (ASTM E2471-05)
Electrostatic Propensity	≤ 3.0 kV (AATCC 134); Permanent Conductive Fiber
Surface Flammability	Passes CPSC FF 1-70 (ASTM D-2859)
Flooring Radiant Panel	Class 1 (mean average CRF: 0.45 w/sq cm or higher) (ASTM E-648)
Smoke Generation	Less than 450 (ASTM E-662)
Colorfastness to Light	≥ 4 after 100 hours (AATCC 16E)
Soil Protection	Application Rate: 2% of Face Weight
Stain Resistance	≥ 8 (AATCC 175-08 Stain Resistance Pile Floor Coverings)

Installation Methods

Peel and Stick	RS Adhesive System - Full Coverage Peel & Stick
Wet Spread	Backing specific Tarkett Adhesives
Installation Method	24"x 24" Vertical Ashlar, 18"x 36", 9"x 36" Vertical Ashlar, Herringbone

Product Notes

- Specifications are subject to nominal manufacturing variances. Material supply and/or manufacturing processes may necessitate changes without notice. Colors may vary slightly from dye lot to dye lot.
- U.S. Patent numbers: 4,849,267; 6,406,574, US 9,988,760 B2
- Chair pads are recommended for optimum textural performance. Absent the use of chair pads, more intensive maintenance will be required for areas in direct contact with chair caster traffic, and some degree of appearance change is to be expected.

Tarkett North America

Technical Services Department
1104 Willowdale Road NW
Dalton, GA 30721
800.248.2878

www.tarkett.com

© 2025 Tarkett USA Inc. 2/2025



IMPERIAL	METRIC	TEST METHOD
Warranty: Lifetime limited warranty against excessive surface wear, static, delamination, edge ravel, zippering, backing resiliency loss & stain resistance.		

ethos® Modular with Omnicoat Technology®

Total Minimum Recycled Content	65.3%			
Pre-Consumer	30.4%			
Post-Consumer	35.0%			
Product Size	24" x 24" Tile (9" x 36" and 18" x 36" also available)			
Secondary Backing	50% Recycled Content			
Intermediate Layer	Fiberglass Reinforced Sealant			
Product Construction	No Delamination per ASTM D-3936			
Secondary Backing Density	65.0	lbs/cu ft	1041	kg/cu m
Secondary Backing Thickness	0.050	inch	1.3	mm
Total Weight	91.1	oz/sq yd +/-5%	3088	g/sq m

Flex-Aire Modular® Cushion

Total Minimum Recycled Content	30.1%					
Pre-Consumer	4.7%					
Post-Consumer	25.4%					
Product Size	24" x 24" Tile (9" x 36" and 18" x 36" also available)					
Secondary Backing	Fiberglass Reinforced Composite Closed Cell Cushion					
Intermediate Layer	Fiberglass Reinforced Sealant					
Product Construction	No Delamination per ASTM D-3936					
Cushion Weight	35.5	oz/sq yd		1203	g/sq m	ASTM D1667
Cushion Density	18.5	lbs/cu ft		296	kg/cu m	ASTM D1667
Cushion Thickness	0.156	inch		4.0	mm	ASTM D1667
Total Weight with RS / Non-RS	111.8	110.7	oz/sq yd +/-5%	3790	3753	g/sq m
Compression Set	Max. 10%					ASTM D1667
Compression Deflection	5 Min.	25 max lbs/sq inch @ 25%	352	1758	g/sq cm	ASTM D1667