

Rockfon Sonar® Rockfon

Final Assembly: Marshall County, Mississippi, USA; Cigacice,

Poland

Life Expectancy: 50 Year(s)

Embodied Carbon: 3.49 - 4.15 kg CO2 eq.

Declared Unit: 1 square meter

End of Life Options: Recyclable (80-95%), Landfill (5-20%)

Ingredients:

Stone wool, biosoluble; Water; Fiberglass; Talc; Syrups, hydrolyzed starch; Glucose; Phenol, polymer with

formaldehyde¹; Barium sulfate; Aluminum hydroxide; Clay; Dodecanedioic acid, polymer with decanedioic acid, hexahydro-2H-azepin-2-one, 1,6-hexanediamine and hexanedioic acid; Caprolactam; Laurolactam; Hexamethylenediamine; Hexanedioic acid; Urea; Limestone; Calcium carbonate; Polyvinyl alcohol; Undisclosed (0.011-0.351%)²; Undisclosed (< 0.314%)²; 2-Propenoic acid, butyl ester, polymer with ethenylbenzene; C12-14-tert-alkylamine, methylphosphonic acid salt; Pulp, cellulose; Urea, polymer with formaldehyde¹; Titanium dioxide; Residual oils (petroleum), solvent-dewaxed; 2-Propenoic acid, 2methyl-, C12-15-branched and linear alkyl esters, polymers with cetyl methacrylate, Me methacrylate, polyethylene glycol methacrylate branched tridecyl ether and stearyl methacrylate; Lubricating oils (petroleum), C>25, solvent-extd., deasphalted, dewaxed, hydrogenated; Undisclosed (< 0.063%)²; Undisclosed (< 0.053%)²; Undisclosed (< 0.047%)²; Undisclosed (0.014-0.036%)²; Acetic acid ethenyl ester, polymer with ethene; Ammonium polyphosphate; n-Butyl acrylate; Styrene; 2-Propenoic acid, butyl ester, polymer with ethenyl acetate; Diethylene Glycol

¹LBC Temp Exception RL-009 - Formaldehyde ²LBC Temp Exception RL-004b - Proprietary Ingredients in Declare

Living Building Challenge Criteria: Compliant

I-13 Red List:

☐ LBC Red List Free

% Disclosed: 99.14% at 100ppm **VOC Content: Not Applicable**

■ LBC Red List Approved □ Declared

I-10 Interior Performance: CDPH Standard Method v1.2-2017

I-14 Responsible Sourcing: Not Applicable

RXI -0019 EXP. 01 FEB 2026 Original Issue Date: 2025