



Applause III #02803

Product Specification

Face Construction	Imperial		Metric		
Construction	Level Loop				
Face Weight	18	oz/sq yd	610.2	g/sq m	
Gauge	1/13		50.4	rows/10 cm	
Stitches per Inch	8.2		32.3	pu/10 cm	
Tuft Density	104.96	tufts/sq in	16.3	tufts/sq cm	
Pile Height Average	0.117	inch	3.0	mm	
Pile Thickness	0.087	inch	2.2	mm	
Total Finished Product Thickness	Powerbond® hybrid carpet: .277 inch				
	ethos® carpet tile with Omnicoat Technology®: .171 inch				
	Flex-Aire™ cushion carpet tile: .277 inch				
Pile Density	7,448	oz/cu yd	275.6	kg/cu m	Kilotex 9.4
Fiber System	Dynex SD® / Dynex® Nylon				
Dye Method	50% Solution Dyed / 50% Yarn Dyed				
Fluorine-Free Soil Protection	Eco-Ensure: C2C Material Health Certification - Gold (v4.1)				
Primary Tufting Substrate	Synthetic Non-Woven				
Pattern Match	Not Required				

Third Party Environmental Certifications

Product	Green Label Plus Certified	NSF 140 SCS Certified	Cradle to Cradle Certified™ v4.0	CERTIFIED asthma & allergy friendly®
ethos carpet tile with Omnicoat Technology	GLP8320	Gold	Bronze	
Flex-Aire cushion carpet tile	GLP6558	Gold		
Powerbond hybrid carpet	GLP9744	Gold		
Powerbond hybrid carpet RS®	GLP9744	Gold		Meets Certification Standards

Recycled Content	Overall	Post-Consumer	Pre-Consumer
ethos carpet tile with Omnicoat Technology	55 - 78%	30 - 43%	25 - 49%
Flex-Aire cushion carpet tile	27 - 45%	22 - 34%	2 - 23%
Powerbond hybrid carpet	12 - 41%	7 - 24%	3 - 33%

Product Testing/Information

Antimicrobial Chemicals	No antimicrobials (EPA Registered pesticides) added to product (ASTM E2471-05)
Electrostatic Propensity	≤ 3.0 kV (AATCC 134); Permanent Conductive Fiber
Surface Flammability	Passes CPSC FF 1-70 (ASTM D-2859)
Flooring Radiant Panel	Class 1 (mean average CRF: 0.45 w/sq cm or higher) (ASTM E-648)
Smoke Generation	Less than 450 (ASTM E-662)
Colorfastness to Light	≥ 4 after 100 hours (AATCC 16E)
Soil Protection	Application Rate: 2% of Face Weight

Installation Methods

Peel and Stick	RS Adhesive System - Full Coverage Peel & Stick
Wet Spread	Backing specific Tarkett Adhesives
Installation Method	24" x 24" Monolithic; 18" x 36" Vertical Ashlar, Herringbone

Product Notes

- Specifications are subject to nominal manufacturing variances. Material supply and/or manufacturing processes may necessitate changes without notice. Colors may vary slightly from dye lot to dye lot.
- U.S. Patent numbers: 4,849,267; 6,406,574, US 9,988,760 B2
- Chair pads are recommended for optimum textural performance. Absent the use of chair pads, more intensive maintenance will be required for areas in direct contact with chair caster traffic, and some degree of appearance change is to be expected.

Tarkett North America

Technical Services Department
1104 Willowdale Road NW
Dalton, GA 30721
800.248.2878

www.tarkett.com



IMPERIAL

METRIC

TEST METHOD

Warranty: Lifetime limited warranty against excessive surface wear, static, delamination, edge ravel, zipping & backing resiliency loss.

ethos® carpet tile with Omniccoat Technology®

Total Minimum Recycled Content	75.8%				
Pre-Consumer	42.8%				
Post-Consumer	33.0%				
Product Size	24" x 24" Tile (18" x 36" also available)				
Secondary Backing	50% Recycled Content				
Intermediate Layer	Fiberglass Reinforced Sealant				
Product Construction	No Delamination per ASTM D-3936				
Secondary Backing Density	65.0	lbs/cu ft		1041	kg/cu m
Secondary Backing Thickness	0.050	inch		1.3	mm
Total Weight	96.1	oz/sq yd +/-5%		3258	g/sq m

Flex-Aire™ cushion carpet tile

Total Minimum Recycled Content	40.1%				
Pre-Consumer	15.8%				
Post-Consumer	24.3%				
Product Size	24" x 24" Tile (18" x 36" also available)				
Secondary Backing	Fiberglass Reinforced Composite Closed Cell Cushion				
Intermediate Layer	Fiberglass Reinforced Sealant				
Product Construction	No Delamination per ASTM D-3936				
Cushion Weight	35.5	oz/sq yd		1203	g/sq m ASTM D1667
Cushion Density	18.5	lbs/cu ft		296	kg/cu m ASTM D1667
Cushion Thickness	0.156	inch		4.0	mm ASTM D1667
Total Weight with RS / Non-RS	116.8	115.7	oz/sq yd +/-5%	3960	3922 g/sq m
Compression Set	Max. 10%				ASTM D1667
Compression Deflection	5 Min.	25 max lbs/sq inch @ 25%	352	1758	g/sq cm ASTM D1667

Powerbond® hybrid carpet

Total Minimum Recycled Content	32.7%				
Pre-Consumer	23.7%				
Post-Consumer	9.1%				
Product Size	6 ft.				
Cushion	Closed Cell Cushion				
Heterogeneous Construction	No Delamination per ASTM D-3936				
Cushion Weight	35.5	oz/sq yd		1203	g/sq m ASTM D1667
Cushion Density	18.5	lbs/cu ft		296	kg/cu m ASTM D1667
Cushion Thickness	0.156	inch		4.0	mm ASTM D1667
Total Weight with RS / Non-RS	78.1	76.7	oz/sq yd +/-5%	2648	2600 g/sq m
Compression Set	Max. 10%				ASTM D1667
Compression Deflection	7 Min.	25 max lbs/sq inch @ 25%	492	1758	g/sq cm ASTM D1667