



## Primary Color #11906

## Product Specification

Face Construction	Imperial		Metric	
Construction	Stratatec® Patterned Loop			
Face Weight	18	oz/sq yd	610.2	g/sq m
Gauge	5/64		50.4	rows/10 cm
Stitches per Inch	9.6		37.8	pu/10 cm
Tuft Density	122.88	tufts/sq in	19.0	tufts/sq cm
Pile Height Average	0.203	inch	5.2	mm
Pile Thickness	0.093	inch	2.4	mm
Total Finished Product Thickness	Powerbond® hybrid carpet: .324 inch			
	ethos® carpet tile with Omnicoat Technology®: .218 inch			
	Flex-Aire™ cushion carpet tile: .324 inch			
Pile Density	6,968	oz/cu yd	257.8	kg/cu m
Fiber System	Dynex SD® Nylon (Permanent Stain Resistance)			
Dye Method	Solution Dyed			
Fluorine-Free Soil Protection	Eco-Ensure: C2C Material Health Certification - Gold (v4.1)			
Primary Tufting Substrate	Synthetic Non-Woven			
Pattern Match	Not required			

### Third Party Environmental Certifications

Product	Green Label Plus Certified	NSF 140 SCS Certified	Cradle to Cradle Certified™ v4.0	CERTIFIED asthma & allergy friendly®
ethos carpet tile with Omnicoat Technology	GLP8320	Gold	Bronze	
Flex-Aire cushion carpet tile	GLP6558	Gold		
Powerbond hybrid carpet	GLP9744	Gold		
Powerbond hybrid carpet RS®	GLP9744	Gold		Meets Certification Standards

Recycled Content	Overall	Post-Consumer	Pre-Consumer
ethos carpet tile with Omnicoat Technology	55 - 78%	30 - 43%	25 - 49%
Flex-Aire cushion carpet tile	27 - 45%	22 - 34%	2 - 23%
Powerbond hybrid carpet	12 - 41%	7 - 24%	3 - 33%

### Product Testing/Information

Antimicrobial Chemicals	No antimicrobials (EPA Registered pesticides) added to product (ASTM E2471-05)
Electrostatic Propensity	≤ 3.0 kV (AATCC 134); Permanent Conductive Fiber
Surface Flammability	Passes CPSC FF 1-70 (ASTM D-2859)
Flooring Radiant Panel	Class 1 (mean average CRF: 0.45 w/sq cm or higher) (ASTM E-648)
Smoke Generation	Less than 450 (ASTM E-662)
Colorfastness to Light	≥ 4 after 100 hours (AATCC 16E)
Soil Protection	Application Rate: 2% of Face Weight
Stain Resistance	≥ 8 (AATCC 175-08 Stain Resistance Pile Floor Coverings)

### Installation Methods

Peel and Stick	RS Adhesive System - Full Coverage Peel & Stick
Wet Spread	Backing specific Tarkett Adhesives
Installation Method	24" x 24" Vertical Ashlar; 18" x 36" Herringbone, Vertical Ashlar

### Product Notes

- Specifications are subject to nominal manufacturing variances. Material supply and/or manufacturing processes may necessitate changes without notice. Colors may vary slightly from dye lot to dye lot.
- U.S. Patent numbers: 4,849,267; 6,406,574, US 9,988,760 B2
- Chair pads are recommended for optimum textural performance. Absent the use of chair pads, more intensive maintenance will be required for areas in direct contact with chair caster traffic, and some degree of appearance change is to be expected.

### Tarkett North America

Technical Services Department  
1104 Willowdale Road NW  
Dalton, GA 30721  
800.248.2878

[www.tarkett.com](http://www.tarkett.com)



IMPERIAL

METRIC

TEST METHOD

**Warranty: Lifetime limited warranty against excessive surface wear, static, delamination, edge ravel, zippering, backing resiliency loss & stain resistance.**

**ethos® carpet tile with Omniccoat Technology®**

Total Minimum Recycled Content	75.8%			
Pre-Consumer	42.8%			
Post-Consumer	33.0%			
Product Size	24" x 24" Tile (18" x 36" also available)			
Secondary Backing	50% Recycled Content			
Intermediate Layer	Fiberglass Reinforced Sealant			
Product Construction	No Delamination per ASTM D-3936			
Secondary Backing Density	65.0	lbs/cu ft	1041	kg/cu m
Secondary Backing Thickness	0.050	inch	1.3	mm
Total Weight	96.1	oz/sq yd +/-5%	3258	g/sq m

**Flex-Aire™ cushion carpet tile**

Total Minimum Recycled Content	40.1%			
Pre-Consumer	15.8%			
Post-Consumer	24.3%			
Product Size	24" x 24" Tile (18" x 36" also available)			
Secondary Backing	Fiberglass Reinforced Composite Closed Cell Cushion			
Intermediate Layer	Fiberglass Reinforced Sealant			
Product Construction	No Delamination per ASTM D-3936			
Cushion Weight	35.5	oz/sq yd	1203	g/sq m ASTM D1667
Cushion Density	18.5	lbs/cu ft	296	kg/cu m ASTM D1667
Cushion Thickness	0.156	inch	4.0	mm ASTM D1667
Total Weight with RS / Non-RS	116.8	115.7	oz/sq yd +/-5%	3960 3922 g/sq m
Compression Set	Max. 10%			ASTM D1667
Compression Deflection	5 Min.	25 max lbs/sq inch @ 25%	352	1758 g/sq cm ASTM D1667

**Powerbond® hybrid carpet**

Total Minimum Recycled Content	32.7%			
Pre-Consumer	23.7%			
Post-Consumer	9.1%			
Product Size	6 ft.			
Cushion	Closed Cell Cushion			
Heterogeneous Construction	No Delamination per ASTM D-3936			
Cushion Weight	35.5	oz/sq yd	1203	g/sq m ASTM D1667
Cushion Density	18.5	lbs/cu ft	296	kg/cu m ASTM D1667
Cushion Thickness	0.156	inch	4.0	mm ASTM D1667
Total Weight with RS / Non-RS	78.1	76.7	oz/sq yd +/-5%	2648 2600 g/sq m
Compression Set	Max. 10%			ASTM D1667
Compression Deflection	7 Min.	25 max lbs/sq inch @ 25%	492	1758 g/sq cm ASTM D1667