

3002 Picnic was tested and met the following flammability requirements:

CA TB 117-2013

ISO/IEC 17025 Third Party Test Report

DATE: February 17, 2022

FILE: DESTEX.A020822A

CLIENT: Design Tex Inc.
357 County Ave
Secaucus, NJ 07094

ATTN: Teesha Prezeau

SAMPLE IDENTIFIED BY CLIENT AS:

Fabric Submitted
Name: Picnic Daisy
Style #: 3002 201
100% Polyurethane
Color Mustard/White

TEST PROCEDURES:

TEST RESULTS:

CALIFORNIA TECHNICAL BULLETIN 117-2013
SECTION 1 COVER FABRIC TEST

	CHAR LENGTH *****	OPEN FLAME *****	SMOULDER TIME OVER 45 MINUTES *****
SPECIMEN 1:	25 mm	N	N
SPECIMEN 2:	21 mm	N	N
SPECIMEN 3:	26 mm	N	N

- a) The mock-up test specimen continues to smolder after the 45-minute test duration: NO
- b) A char develops more than 1.8 inches (45 mm) in any direction from the cigarette on the cover fabric measured from its nearest point: NO
- c) The mock-up test specimen transitions to open flaming: NO

RESULTS: **PASS**

A material is considered to pass or fail based on the following criteria:

1. A single mock-up test specimen fails to meet the requirements of this test procedure if any of the following criteria occurs:
 - a) The mock-up test specimen continues to smolder after the 45-minute test duration.
 - b) A char develops more than 1.8 inches (45 mm) in any direction from the cigarette on the cover fabric measured from its nearest point.
 - c) The mock-up test specimen transitions to open flaming.
2. The cover fabric passes the test if three initial mock-up specimens pass the test, i.e., the cigarettes burn their full length and the mock-ups are no longer smoldering.
3. If more than one initial specimen fails, the cover fabric fails the test.
4. If any one of the three initial specimens fails, repeat the test on an Additional three specimens.
5. If all three additional specimens pass the test, the cover fabric passes the test.
If any one of the three additional specimens fails, the cover fabric fails the test.

ISO/IEC 17025 Third Party Test Report

FILE: DESTEX.A020822A

SAMPLE IDENTIFIED BY CLIENT AS:

Fabric Submitted
Name: Picnic Daisy
Style #: 3002 201
100% Polyurethane
Color Mustard/White

NFPA 260

STANDARD METHODS OF TEST AND CLASSIFICATION SYSTEM FOR
CIGARETTE IGNITION RESISTANCE OF COMPONENTS OF UPHOLSTERED FURNITURE

SECTION 6.1 COVER FABRIC

	<u>CHAR LENGTH (mm)</u>
Sample #1:	23
Sample #2:	25

RESULTS:

Evidence Of Ignition: No.


RESULTS: N/A

- 6.1.9. If an obvious ignition occurs on any of the three specimens, the smoldering materials shall be extinguished, and the sample shall be recorded as a Class II cover fabric based on the results of this test.
- 6.1.10. If no obvious ignition occurs, the char on the vertical panel measured from the original crevice position to the highest part of the destroyed or degraded cover fabric shall be recorded to the nearest 2.5 mm.

7.2 Cover Fabric Classification

- 7.2.1. **Class I** - Class I cover fabric shall meet the criteria of 7.2.1.1 and 7.2.1.2.
- 7.2.1.1. When subjected to the cover fabric test, a specimen shall show no evidence of ignition on any test assembly.
- 7.2.1.2. The vertical char on any of the three specimens shall not exceed 45 mm.
- 7.2.2. **Class II** - Cover fabrics that do not meet Class I criteria shall be designated as Class II.

Signed For The Company By


Joseph Lin
Laboratory Manager

CS/02




Stacy Sadowy
Quality Assurance Manager

