

# LIGHT + SHADOWS

## Trimline

Modular Tile

### Construction

Tufted, Textured Loop

### Tile Size

50 cm x 50 cm (19.7" x 19.7")

### Yarn Type

Milliken-Certified WearOn® Nylon

### Stain Resist / Soil Release

StainSmart®

### Dye Method

PrintWorks™ Precision Dyeing

### Tufted Face Weight

15.0 oz/yd² (508.6 g/m²)

### Gauge

1/12

### Stitches Per Inch

9.8

### Tufts

117.6/in² (1,859/100 cm²)

### Finished Pile Thickness

0.080" (2.03 mm)

### Average Density (Finished)

6,541

### Standard Backing

PVC-Free WellBAC® Comfort Cushion

Available with TractionBack®

### Recycled Content by Total Weight

Standard Backing NSF 140 Gold:  
56.3% Pre-Consumer, 8.1% Post-ConsumerNSF 140 Platinum Backing Option:  
45.8% Pre-Consumer, 18.5% Post-Consumer

### Embodied Carbon

7.5 (kg CO<sub>2</sub>e)/m²

### Nominal Total Thickness

0.280" (7.4 mm)

### Nominal Total Weight

89.3 oz/yd² (3,028 g/m²)

### Flammability (Radiant Panel ASTM-E-648)

≥ 0.45 (Class I)

### Smoke Density (NFPA-258-T or ASTM-E-662)

≤ 450

### Methenamine Pill Test (CPSC FF-1-70 or ASTM D 2859)

Self-Extinguishing

### Lightfastness (AATCC 16E)

≥ 4.0 at 80 Hours

### Crocking (AATCC 165)

≥ 4.0 Wet or Dry

### Static Electricity (AATCC-134) 20% R.H., 70° F.

≤ 3.5 KV, Permanent Conductive Fiber

### Texture Appearance Retention Rating (TARR)

Severe Traffic End-Use Applications

### Recommended Maintenance

MilliCare® Textile and Carpet Care Service Network

### Indoor Air Quality—CRI Green Label Plus™

GLP0793, Carpet Category 5Y

### Recommended Installation Method(s)

Monolithic

### WARRANTIES

Lifetime Face Fiber Wear

Lifetime Antistatic

Lifetime Floor Compatibility

Lifetime Color Pattern Permanency

Lifetime Floor Release

Lifetime Cushion Resiliency

Lifetime Moisture Resistance

Lifetime Delamination of Backing

Lifetime Staining/Soiling (StainSmart®)

Lifetime Dimensional Stability

Lifetime Tuft Bind

Lifetime Edge Ravel

Flammability



## Declare.



This cushion-back carpet tile product is covered by one or more patents, published applications and/or patents pending. Specifications are subject to normal manufacturing tolerances and may be changed without prior notice. Copies of actual test results are available upon request.