

# THE GALLERY

Mod

Modular Tile

## Construction

Tufted, Textured Loop

## Tile Size

50 cm x 50 cm (19.7" x 19.7")

## Yarn Type

Milliken-Certified WearOn® Nylon

## Stain Resist / Soil Release

StainSmart®

## Dye Method

PrintWorks™ Precision Dyeing

## Tufted Face Weight

15.0 oz/yd<sup>2</sup> (508.6 g/m<sup>2</sup>)

## Gauge

1/12

## Stitches Per Inch

9.8

## Tufts

117.6/in<sup>2</sup> (1,821/100 cm<sup>2</sup>)

## Finished Pile Thickness

0.080" (2.03 mm)

## Average Density (Finished)

6,541

## Standard Backing

PVC-Free WellBAC® Comfort Cushion

Available with TractionBack®

## Recycled Content by Total Weight

Standard Backing NSF 140 Gold:  
57.3% Pre-Consumer, 7.7% Post-Consumer

NSF 140 Platinum Backing Option:  
46.9% Pre-Consumer, 18.0% Post-Consumer

## Embodied Carbon

7.5 (kg CO<sub>2</sub>e)/m<sup>2</sup>

## Nominal Total Thickness

0.280" (7.1 mm)

## Nominal Total Weight

89.2 oz/yd<sup>2</sup> (3,024 g/m<sup>2</sup>)

## Flammability (Radiant Panel ASTM-E-648)

≥ 0.45 (Class I)

## Smoke Density (NFPA-258-T or ASTM-E-662)

≤ 450

## Methenamine Pill Test (CPSC FF-1-70 or ASTM D 2859)

Self-Extinguishing

## Lightfastness (AATCC 16E)

≥ 4.0 at 80 Hours

## Crocking (AATCC 165)

≥ 4.0 Wet or Dry

## Static Electricity (AATCC-134) 20% R.H., 70° F.

≤ 3.5 KV, Permanent Conductive Fiber

## Texture Appearance Retention Rating (TARR)

Severe Traffic End-Use Applications

## Recommended Maintenance

MilliCare® Textile and Carpet Care Service Network

## Indoor Air Quality—CRI Green Label Plus™

GLP0793, Carpet Category 5Y

## Recommended Installation Method(s)

Monolithic

## WARRANTIES

Lifetime Face Fiber Wear

Lifetime Antistatic

Lifetime Floor Compatibility

Lifetime Color Pattern Permanency

Lifetime Floor Release

Lifetime Cushion Resiliency

Lifetime Moisture Resistance

Lifetime Delamination of Backing

Lifetime Staining/Soiling (StainSmart®) Lifetime

Dimensional Stability

Lifetime Tuft Bind

Lifetime Edge Ravel

Flammability



Declare.



This cushion-back carpet tile product is covered by one or more patents, published applications and/or patents pending. Specifications are subject to normal manufacturing tolerances and may be changed without prior notice. Copies of actual test results are available upon request.